




## **SUPERIOR PERFORMANCE**

IN EXTREME TEMPERATURES







# ZERO DEFECT CHOICE







Prince Pipes is not about creating products that are different but providing solutions that make a difference. From our zero defect manufacturing process that involves using recycled plastic to designing and equipping our plants with solar panels and various other energy saving manufacturing techniques, our endeavor has always been to further bring down the emission levels. Our strong belief in the concept of "better lasts longer" has not only helped us deliver premium quality products but also ensure lesser consumption. Together with our channel partners and plumbers, we are sure to leave a strong legacy for the generations to come.



### THE JOURNEY

#### 2021

- Manufacturing unit commissioned at Sangareddy,
   Telangana. To strengthen our strategic
   presence in Southern India
  - Prince Pipes has been awarded Brand of The Year - Pipes at Realty + INEX Awards 2021

#### 2019

- Manufacturing unit at Jobner, Rajasthan to cater to increasing volume demand
  - Company successfully got listed on BSE and NSE

#### 2017

- Prince Pipes became a Public Limited Company.
- Economic Times Polymers Award (Excellence in Plastics) for excellence in building and construction (plumbing) in the large enterprises category.

#### 2015

- Mr. Jayant Chheda received the "Life time Achievement Award" at Vinyl India Conference.
- "IMEA Award" for Haridwar factory by Frost & Sullivan.

### 2012

Prince Pipes acquired "Trubore"- a renowned brand of southern India from Chemplast Sanmar Group along with their two manufacturing units at Kolhapur & Chennai.

### 2008

Manufacturing unit at Haridwar (Uttarakhand) was established to cater to the increasing demand for Prince Pipes products.

### 2000

Manufacturing unit at Dadra (Silvassa - D & N.H) was established to augment the pipe manufacturing capacity by setting up a new extrusion unit.

### 1995

Manufacturing unit at Athal (Silvassa-D & N.H) was established to set-up a large scale Injection Moulding Unit which marked the beginning for Prince Pipes to be one of the market leaders in PVC Fittings.

### 2020

- Prince Pipes Product collaborates with Lubrizol the world's largest manufacturers and inventors of CPVC compounds.
- Technical collaborates with Tooling holland A global leader in plastic moulds manufacturing

### 2018

Prince Pipes announced bollywood actor Akshay Kumar as its brand ambassador.

#### 2016

Mr. Parag Chheda presented with the Inspiring Business Leader Award by Economic Times.

#### 2014

Prince Pipes received "Asia's Most Promising Brand Award" by World Consulting and Research Corporation Delhi.

### 2010

- Winner of Best SME at the "Emerging India Awards 2010" by ICICI Bank, CNBC TV 18 & CRISIL.
- Winner of "Outstanding Quality Contribution In Pipes Sector" by Bloomberg EPC world.

### 2005


Prince Pipes achieved the ₹100 Crore benchmark.

### 1998

ISO Certification earned by ensuring compliance to every step of the quality management system.

### 1987

- Mr. Jayant Chheda commenced manufacturing unit of PVC Products.
- 1st PVC Fittings Manufacturing Unit initiated to provide total piping solutions.



F # I P a F # I P a CONTENTS PY 2 4 1 PY 2 4 1 

Manufacturing Units

Certifications

**Greenfit PP-R Certifications** 

Introduction

**Product Characteristics** 

Standard Working Conditions & Service Life

Long Term Performance

• Reference Standards • Types of PP-R Pipes Features, Benefits & Applications

• Standards Pipes Dimensions Fittings Dimensions

Brass Insert Fittings Dimensions

Accessories

**Quality Assurance Tests** 

**Technical Details** 

Design Guidelines

Pressure Loss Table

Jointing Methods

DO's & DON'Ts

• Recommended Time for PP-R Fusion Joints Hole Repairing • Testing the Installation

Chemical Resistance Chart

Installation Images

## **MANUFACTURING UNITS**















## **CERTIFICATIONS**















### **GREENFIT PP-R CERTIFICATIONS**



### WATER REQULATIONS ADVISORY SCHEME LTD. (WHATE MATERIAL APPROVAL

POLYPROPYLENE - COMPONENTS.

The Spheme reserves the right to review approval.

Approval 1410030 is valid between December 2011 and December 2021.

An entry, as above, will assorbegly to instablish the Water Fishiga Directory on line under the poster healthd, "Materials which have present hid basis of effect or ventor quality".

The Directory may be found at page atto or abstraction

To him fundation, Manay Sanare (a. Suptace) of Refere to SMESS Reprinted of the SE Local Class, State Street, State SMESS SET SMESS Reprinted of the SE Local Class SMESS SMES

Prince Pipes & Pitings Per, Ltd. Shapira No-15-III. 15-III-18-15, Saferegue.



APPROVAL NUMBER: 10/05HI APPROVAL HOLDER: PRINCE PIPES & RETUNOS PVT. LTD.

An entry, as above, will assorbingly an industral in the Water Fittings Directory on one under the section handed, "Materials whose passed full feets of effect or veter guidity".



भारतीय मानक ब्यूरो BUREAU OF INDIAN STANDAROS

देहरादून शासा काचीलय

DEHRADUN BRANCH OFFICE

Vislinu Vilhar, Dehradun - 248001 Phones : 7617777270, 7617777278 E-Mail: ghoofths.my.kt Web: http://www.bls.org.in GST No. OSAAATBOH31G1ZH

Address: UCF Sadan, Ground Floor,

Block- D, Deep Hager Road

पंजीकृतरपारती

**(FIRST WIGH: DHBO/CML-3602447** 

Renting 2 AUG 2021

दिश्यः प्रमाणन मृहदंबन संख्या सीरमाणम- ३६०२४४७ वर नवीनीकरण

M/s. Prince Pipes and Fittings Ltd., Khasra No.1548-1549/465, Salempur Metidood-2 Off 50 meter Wide Road, Bahadmbad, SIDCLI, Highway Road,

Diss-Haridwan. Uttarakhond

।. कृपका अपने ऑपलाइन नवीनीकरण अवेदन का अवनीकन क्षेत्र इसे यह जानकारी देने हुए प्रमुख्ता है कि आपके प्रमाणन नामगेंत का दिनांत 01-08-2021 में 31-07-2022 तक नवीवरण हो नमा है।

कृत्रसा स्वास दें कि यह लायमेल उपयोक्त निर्मित्र कारिक्ष के बाद समाग्र हो जाएमा: का: आपने अनुरोध है कि अप अपना मानवेत सर्वतिकत्य कराने के निए आकेत्र सुन्य, शार्षिक शुन्य तथा मुहारीकद सुन्य के माथ जनके नवीनीकार की तिकि से बार से कर एक बात पूर्व जीवनाइए अवेदर करें।

3. मारबोस सबीवीकरण के संदर्भ में पूर्वकर सीट बनांव 14 संख्य है | इसे कृषका जरने चार प्रचान्ध सूच लायमेंथ के माथ जीत है।

SPREED

7-5-6 (मीक्षम्बद इमरापीय) वैज्ञाविक- सी

संबद्ध: पर्यान

भारतीय मानक व्यूरो BUREAU OF INDIAN STANDARDS

देहरादून शाखा कार्यालय DEHRADUN BRANCH OFFICE Address: UCF Sadan, Ground Floor,

Block- D, Deep Nagar Road, Phones: 7617777270, 7617777278 E-Mail: dhbodhbis.acv.in Web: http://www.bis.gra.in GST No. 05AAATB0431G12H

बचुत्रति संख्यासी एव् / एक- 3602447 वा संजयक

सी प्रम/ एस संख्या CM/L-No	लाइसँसफारी का यता संदित ज्याम Name of the Licensee with the Factory Address	उत्पाद का माम Name of the Product	आरतीय मानक संद्रमा Indian Standard No.
3602447	Mis. Prince Pipes and Finings Ldd Khanra No. 1548–1549/46.5. Salempar Mehdood-2 Off Streeter Wide Road, Bahadrabod, SIDCUL. Highway Road, Dista-Haridwar, Literalihand	Polypropylene-random copolymer pipes for hot and cold water supplies -	15 15801 : 2008

पुष्टांकम संख्या 14 दिमांक Indorsement No. 14 Dated 11 - 08 - 202 ।

बनुवाणि ३। कुणाई २०२१ तथा प्राप्त का । Wherem, the licence was valid upto Thirty First July Two Thousand Twenty One.

जब, नवीनीकरण के परिभावरकरण, अनुसीवन गंकता 53 में विश वल अनुसारे की केवता 81 जनमा 2021 में 31 जुलाई 2022 वरू बड़ा दो नवी है।

Now, consequent upon emercal, the salisity of the licence given in the Endocument No. 23 has been extended from First August Two Thousand Twenty One to Thirty First July Two-Thousand Twenty Tweeth Two.

अनुप्रति की अन्य नमें नामान रहेंथी । Other terms and conditions of licence remain same.

पद्मितिन प्राप्तिकारी के समाधार

andamil सुधीर विश्वास वेज्ञानिक- ई एवं उनुष्ठ कार्यानक

### INTRODUCTION

### **PREFACE**

Progressive development of civilization results in people aspiring for better living standards. This can be met by using new materials in building industry which are more fit for use as well as more aesthetic than the traditional ones.

Today, the use of plastic products in construction as well as other industries is extremely widespread. Rapid changes in plastic raw materials and processing techniques provide advantages which cause these materials to be preferred in place of traditional construction and industrial application materials. One of these innovations is plumbing pipes and fittings produced out of POLYPROPYLENE RANDOM COPOLYMER (PPRC or commonly known as PP-R) material.

The superior physical characteristics of PP-R material, such as working temperatures up to 95°C, excellent chemical resistance as well as providing a definite solution to oxidation and calcification, make PP-R an ideal material, primarily for hot and cold water plumbing systems in buildings and industrial piping installations, ensuring a high quality performance.

PRINCE has been a leading manufacturer of uPVC piping systems since last 3 decades. Understanding the needs of the customer, PRINCE Piping Systems has established manufacturing of pipes, fittings & valves in PP-R material, using the best available technologies. PRINCE Piping Systems is proud to offer a complete range of high quality and reliable PP-R piping system for the modern construction industry.

### WHY PRINCE GREENFIT PP-R

The primary advantages which make GREENFIT PP-R Piping Systems preferred over traditional ones are:-

Material Properties	Advantages
Lightweight	Easy to handle, transport and install. Saves Labour cost.
Better Corrosion Resistance	No scaling, can withstand higher 'pH' values.
Nontoxic, Hygienic 'Green product'	Safe for drinking water. No harmful effect to humans & ecology.
High Vicat Softening Temperature	Ensures thermal stability for hot water application.
UV resistant	Three layer pipes are suitable for outdoor installations, exposed to direct sunlight.
Good Thermal Insulation	Ensures lower heat losses & saves energy up to 15%
Good Chemical Resistance	Suitable for most of the industrial liquids.
Better Impact Strength	Higher stiffness than the standard pipes.
Heat Fusion Welding (no use of solvent)	Results in a homogeneous plastic system ensuring leak proof joint. Safe and reliable to use for concealed and exterior installations. Saves considerable jointing time.
Better Noise Insulation	Reduces water hammer sound.
Bacteriologically Neutral	Can be used underground. Also the fluid inside remains free from bacterial growth.
Very Less Coefficient of Friction	Low-pressure drop. Extremely high flow properties. Reduces pumping cost.
Resilience	Suitable for use in seismic areas.
Good Abrasion Resistance	Allow higher flow velocities of fluid up to 5 m/sec.
High Volume Resistivity	Poor conductor of electricity. No effect of stray currents.
Long life	Can exceed 50 years when operating under rated temperature and pressure conditions.
Linear Expansion	75% less linear expansion than standard pipes.

All the above advantages make PRINCE GREENFIT PP-R piping system the most cost effective solution compared to any other plumbing system.



### **COMPARISON BETWEEN DIFFERENT PIPING SYSTEMS**

Property	Copper	CPVC	Galvanised Iron	HDPE	PRINCE GREENFIT PP-R
Type of joint	Soldering	Solvent welding	Threaded	Butt fusion	Poly-fusion welding. For transition joints, fittings with threaded metal inserts, are also available.
Installation	Time consuming & requires skill.	Easy to install, saves time & labour.	Tedious & time consuming.	Needs skilled abour.	Easy to install, saves time & labour.
Corrosion resistance	Not resistant	Free from corrosion.	Not resistant	Good	Free from corrosion.
Chemical resistance	Poor	Resistant to most of the chemicals.	Not resistant	Good	Excellent chemical resistance even at higher temperatures.
Scale formation	Common	No scaling  Very common impurities in water		No scaling	
Suitability in cold areas - sub- zero temperatures	Not suitable, Pipe bursts.	Impact strength considerably reduces at lower temperature & hence not suitable.	Not suitable. Pipe bursts.	Not suitable, Pipe cracks.	Most suitable due to typical elastic nature and good impact strength.
Insulation requirements	Essential	Not required	Essential	Required	Insulation is necessary at sub zero temperature.
Impact strength	Less	Less (brittle nature)	Excellent	Average	High impact strength.
Life span under rated pressure & temperature	20 - 30 years	30 - 40 years	5 -15 years	20-30 years	Can exceed 50 years.
Behavior in Fire	Resistant but de-shapes or punctures.	High percentage of chlorine and toxic gases are generated which are harmful.	Resistant	Not resistant	Melts like all other plastics, but no generation of any toxic gases.

## **PRODUCT CHARACTERISTICS**

### **GREENFIT PP-R TECHNICAL SPECIFICATIONS**

### **PHYSICAL PROPERTIES**

Property	roperty Test Method		Value
Density, at 27°C	IS 12235 (Part 14)	Kg /m³	900 - 910
Melt Flow Rate at 230° C/2.16 kg IS 13360 Part 4/Sec 1		g/10 min	< 0.25
Viscosity	ISO 1191, ISO 1628 T3	-	-

### **THERMAL PROPERTIES**

Property	Test Method	Units	Value
Thermal Conductivity	DIN 52612	W/m.K	0.24
Specific heat, at 23°C	Calorimeter	KJ/kg.K	2.0
Coefficient of linear expansion DIN 53752		mm/M°C	1.5 x 10 <sup>-4</sup>
VICAT Softening Temperature	ISO 306	°C	132
Melting Temperature Range	ISO 3146	°C	140 –150

### **MECHANICAL PROPERTIES**

Property	Test Method	Units	Value
Tensile Stress at Yield (50mm/	ISO 527-1, 2	MPa	24
minute)	150 527-1, 2	IVIFa	24
Tensile Strain at Yield (50mm/	ISO 527-1, 2	%	>50
minute	100 327 1, 2	70	>00
Tensile modules (secant)	ISO 527-1, 2	MPa	850
Flexural Modulus	ASTM D 790	MPa	850
Tear Strength	ISO 527	MPa	40
Elongation at tear	ISO 527	%	800
Shore D Hardness	DIN 53 505	-	65
Pipe Friction factor	-	-	0.007
CHARPY Impact Strength - 23°C	IS0179/leA	KJ/m²	22
0°C	IS0179/leA	KJ/m²	4.0
-30°C	IS0179/leA	KJ/m²	2.5

### **PHYSICAL PROPERTIES**

Property	Test Method	Units	Value
Di electric constant	DIN 53483	-	2.3
Volume Resistivity	DIN 53482 Ohm-cm		> 1 x 1016
Di electric strength DIN 53481		KV/mm	> 20





### STANDARD WORKING CONDITIONS & SERVICE LIFE

Long-term performance curve shows the behavior of a pipe line depending on pressure and operating temperature. It establishes the average life expectancy of a pipe line as a function of hoop stress acting on the pipe walls. Hoop stress is in proportion with the pressure according to the following formula:

### WHERE:

(d-s)

 $\delta$  = hoop stress (MPa)

 $S_f = Safety factor$ 

p = Internal pressure (MPa)

 $\delta = S_f X p X$ 

d = Outside diameter of pipe (mm)

s = Wall thickness of pipe (mm)

If we extrapolate the hoop stress from the long term performance curve and apply the formula using 1.5 safety factor, the admissible operating pressures are obtained as given in the tables.

#### **ADMISSIBLE OPERATING PRESSURE**

ပွ	/ears	Pipe Series according to DIN 8077/8078			
Temperature °C	Service Life in Years	SDR 11 - PN 10	SDR 7.4 - PN 16	SDR 6 - PN 20	
шре	ice L	S	afety-factor 1	5	
Те	Servi	Nominal p	oressure for P (kgs/cm²)	P-R pipes	
	1	17.6	27.8	35.0	
	5	16.6	26.4	33.2	
10°C	10	16.1	25.5	32.1	
10 0	25	15.6	24.7	31.1	
	50	15.2	24.0	30.3	
	100	14.8	23.4	29.5	
	1	15.0	23.8	30.0	
	5	14.1	22.3	28.1	
0000	10	13.7	21.7	27.3	
20°C	25	13.3	21.1	26.5	
	50	12.9	20.4	25.7	
	100	12.5	19.8	24.9	
	1	12.8	20.2	25.5	
	5	12.0	19.0	23.9	
2000	10	11.6	18.3	23.1	
30°C	25	11.2	17.7	22.3	
	50	10.9	17.3	21.8	
	100	10.6	16.9	21.2	
	1	10.8	17.1	21.5	
	5	10.1	16.0	20.2	
40°C	10	9.8	15.6	19.6	
40°C	25	9.4	15.0	18.8	
	50	9.2	14.5	18.3	
	100	8.9	14.1	17.8	

* Bracketed values apply where testing can be shown to
have been carried out for longer than 1000 hours at 950°C

	Irs	Pipe Series according to DIN			
ပွ	/ea	8077/8078			
nre	ii /	SDR 11 -	SDR 7.4 -	SDR 6 -	
aratı	ife	PN 10	PN 16	PN 20	
Temperature °C	ice L	S	afety-factor 1.	.5	
H <sub>e</sub>	Service Life in Years	Nominal p	oressure for P (kgs/cm²)	P-R pipes	
	1	9.2	14.5	18.3	
	5	8.5	13.5	17.0	
50°C	10	8.2	13.1	16.5	
50 C	25	8.0	12.6	15.9	
	50	7.7	12.2	15.4	
	100	7.4	11.8	14.9	
	1	7.7	12.2	15.4	
	5	7.2	11.4	14.3	
60°C	10	6.9	11.0	13.8	
	25	6.7	10.5	13.3	
	50	6.4	10.1	12.7	
	1	6.5	10.3	13.0	
	5	6.0	9.5	11.9	
70°C	10	5.9	9.3	11.7	
	25	5.1	8.0	10.1	
	50	4.3	6.7	8.5	
	1	5.5	8.6	10.9	
80°C	5	4.8	7.6	9.6	
80 C	10	4.0	6.3	8.0	
	25	3.2	5.1	6.4	
	1	3.9	6.1	7.7	
95°C	5	2.5	4.0	5.0	
	(10)*	(2.1)*	(3.4)*	(4.2)*	


#### **Explanations:**

= Recommended application - cold water installation

= Recommended application - hot water installation

= Recommended application - central heating installation

### LONG TERM PERFORMANCE








### REFERENCE STANDARDS

Standards	
IS 15801	Polypropylene-Random Copolymer Pipes For Hot & Cold Water Supplies
DIN 16962	
a) Part 5	Pipe fittings and joint assemblies for polypropylene (PP) pressure pipes. General quality requirements and testing.
b) Part 6	Pipe joints and Elements for Polypropylene (PP) Pressure Pipelines. Types 1 and 2 Injection Moulded Elbows for Socket-welding Dimension.
c) Part 7	Pipe joints and Elements for Polypropylene (PP) Pressure Pipelines. Types 1 and 2 Injection Moulded Tee Pieces for Socket-welding Dimension.
d) Part 8	Pipe joints and Elements for Polypropylene (PP) Pressure Pipelines. Types 1 and 2 Injection Moulded Sockets & Caps for Socket-welding Dimension.
e) Part 9	Pipe joint assemblies and fittings for types 1 and 2 polypropylene (PP) pressure pipes. Injection moulded reducers & nipples for socket welding Dimensions.
f) Part 10	Pipe joint assemblies and fittings for types 1 to 3 polypropylene (PP) pressure pipes. Injection-moulded fittings for butt welding Dimensions.
IS 9845	Method of analysis for determination of specific and/or overall migration of constituents of plastic materials and articles intended to come into contact with foodstuffs.
IS 10500	Specification for polypropylene and its copolymers for its safe use in contact with food stuffs, Pharmaceuticals and drinking water.

### **TYPES OF PP-R PIPES**

These pipes are used for conveying hot and cold water/fluids/chemicals/ compressed air in various plumbing installations such as,

- (A). Single layer (Green/ Blue Colour) Greenfit PP-R pipes for indoor installations.
- (B). 3 Layer Greenfit PP-R pipes for outdoor installations.
  - Outer layer (Green / Blue Colour) Greenfit PP-R is UV resistant, which makes the pipes suitable for usage under direct sunlight.
  - Inner layer (White Colour Greenfit PP-R is antimicrobial which adds to safety against inside bacterial growth.)
  - Middle layer (Off White Colour) Greenfit PP-R ensures the required strength of the pipes.
- (C). 3 Layer Greenfit PP-R thermax pipe has a specially formulated middle layer to reduce linear expansion of pipe due to temperature variance and to improve impact strength



### FEATURES AND BENEFITS FOR GREEN PP-R



Proven hot & cold water performance from -20°C to 95°C



No scaling. Can withstand higher 'pH' values



UV resistant triple layered pipes are suitable for outdoor installations that are exposed to direct sunlight



Good chemical resistance suitable for most industrial liquids



Heat-fusion jointing results in homogenous plastic system ensuring leak-proof joints



Very less coefficient of friction, ensures high flow properties, reduce pumping cost



Antimicrobial inside layer of 3 layered pipe adds to safety against bacterial growth ensuring safe drinking water



Specially formulated thermex pipes reduce linear expansion / contraction of pipes due to temperature variance, ensuring suitability for outdoor application



Low maintenance cost.

### APPLICATIONS FOR GREEN PP-R



Indoor & outdoor installations of hot & cold water piping systems in residential, commercial & buildings



Heating system inside buildings including floor, wall & radiator heating



Aggressive Chemicals & Pharmaceuticals Piping systems for conveyance of aggressive fluids in Industries



Solar water heating systems



Drinking water & liquid food transportation

### FEATURES AND BENEFITS FOR BLUE PP-R



Proven hot & cold water performance from -20° C to 95°C



UV resistant triple layered pipes are suitable for outdoor installations that are exposed to direct sunlight



Heat-fusion jointing results in homogenous plastic system ensuring leak-proof joints



These joints are better than the conventional metal and aluminium joints



Smooth inner surface, ensuring least friction for the flowing air




Negligible creation of moisture leading to corrosion free pipes



Low thermal conductivity

### APPLICATIONS FOR BLUE PP-R





Secondary usages

- Instrument Air
- Nitrogen Air
- Vacuum Pipingwall






## **STANDARDS FOR PIPES AND FITTINGS**

	Pipes						
Type	Size (mm)	Working Pressure (Kg/cm2)	Class	Standard	Colour	End Connection	
Green PP-R	20 to 160	10, 16 & 20	SDR 11 (PN 10), SDR 7.4 (PN 16), SDR 6 (PN 20)	IS: 15801	Single layer pipes - Green,     Triple layer pipe - Outer layer in green, inner layer in white     Thermex Pipe - Outer layer in green, middel layer in light grey, inner layer in white	Poly-fusion welding joint	
Blue PP-R			555 (11125)		Triple layer pipe - Outer layer in Blue, inner layer in White		

	Fittings					
Туре	Size (mm)	Working Pressure (Kg/cm2)	Standard	Colour	End Connection	
Green PP-R	20 to 160	20.8.05	Green		Socket ends suitable for poly-fusion welding.     Socket ends suitable for poly-fusion welding.	
Blue PP-R	20 10 160	20 & 25 DIN:16962 Blue		Blue	For transition joints, fittings with threaded metal inserts.	

## **PIPES DIMENSIONS**



Nomin	al Bore	Outside Diameter	SDR 11	(PN-10)	SDR 7.4	(PN-16)	SDR 6	(PN-20)
(mm)	(inch)	(mm)	d	S	d	S	d	s
(111111)	(IIICII)	(111111)	(mm)	(mm)	(mm)	(mm)	(mm)	(mm)
20	1/2	20.00	16.20	1.90	14.40	2.80	13.20	3.40
25	3/4	25.00	20.40	2.30	18.00	3.50	16.60	4.20
32	1	32.00	26.20	2.90	23.20	4.40	21.20	5.40
40	1 1/4	40.00	32.60	3.70	29.00	5.50	26.60	6.70
50	1 1/2	50.00	40.80	4.60	36.20	6.90	33.40	8.30
63	2	63.00	51.40	5.80	45.80	8.60	42.00	10.50
75	2 1/2	75.00	61.40	6.80	54.40	10.30	50.00	12.50
90	3	90.00	73.60	8.20	65.40	12.30	60.00	15.00
110	4	110.0	90.00	10.00	79.80	15.10	73.40	18.30
160	6	160.0	130.80	14.60	116.20	21.90	106.80	26.60

## **FITTINGS DIMENSIONS**


Fusion Weld Joint





## **COUPLER**

Size (mm)	ØD	L	Z	н
20	19.50	14.50	4.00	33.00
25	24.50	16.00	4.00	36.00
32	31.50	18.00	4.00	40.00
40	39.45	20.50	4.00	45.00
50	49.45	23.50	4.00	51.00
63	62.50	27.50	4.00	59.00
75	74.90	30.00	4.00	64.00
90	89.90	33.00	5.00	71.00
110	110.00	37.00	5.00	79.00
160	159.00	48.00	5.00	101.00








## ELBOW 90°

Size (mm)	ØD	L	Z
20	19.50	14.50	11.00
25	24.50	16.00	13.50
32	31.50	18.00	17.00
40	39.45	20.50	21.00
50	49.45	23.50	26.50
63	62.50	27.50	32.50
75	74.90	30.00	41.00
90	89.90	33.00	48.50
110	110.00	37.00	58.00
160	159.00	48.00	26.00



### **REDUCING ELBOW 90°**

Size (mm)	ØD1	ØD2	L1	L2	Z1	Z2
25 X 20	24.50	19.50	16.00	14.50	13.50	15.00
32 X 25	31.50	24.50	18.00	16.00	17.00	19.00
32 X 20	31.50	19.50	18.00	14.50	17.00	20.50
40 X 32	39.45	31.50	20.50	18.00	21.00	20.50
40 X 20	39.45	19.50	20.50	14.50	21.00	20.50
40 X 25	39.45	24.20	20.50	16.00	21.00	25.50
63 X 40	62.50	39.45	27.50	20.50	32.50	39.50










## ELBOW 45°

Size (mm)	ØD	L	Z
20	19.50	14.50	5.00
25	24.50	16.00	6.00
32	31.50	18.00	7.50
40	39.45	20.50	9.50
50	49.45	23.50	11.50
63	62.50	27.50	14.00
75	74.90	30.00	38.50
90	89.90	33.00	46.00
110	110.00	37.00	56.00
160	159.00	48.00	-








## **EQUAL TEE**

Size (mm)	ØD	L	Z	Н
20	19.50	14.50	11.00	51.00
25	24.50	16.00	13.50	59.00
32	31.50	18.00	17.00	70.00
40	39.45	20.50	21.00	83.00
50	49.45	23.50	26.50	100.00
63	62.50	27.50	32.50	120.00
75	74.90	30.00	38.50	137.00
90	89.90	33.00	46.00	158.00
110	110.00	37.00	56.00	186.00
160	159.00	48.00	24.00	150.00







### **REDUCING TEE**


Size (mm)	ØD1	ØD2	L1	L2	Z1	Z2	Н
25 X 20	24.50	19.50	16.00	14.50	13.50	13.50	59.00
32 X 25	31.50	24.50	18.00	16.00	14.00	18.00	64.00
32 X 20	31.50	19.50	18.00	14.50	14.00	19.50	64.00





### **REDUCING TEE**

Size (mm)	ØD1	ØD2	L1	L2	Z1	Z2	Н
40 X 32	39.45	31.50	20.50	18.00	21.00	21.00	83.00
40 X 25	39.45	24.50	20.50	16.00	21.00	21.00	83.00
40 X 20	39.45	19.50	20.50	14.50	21.00	21.00	83.00
50 X 40	49.45	39.45	23.50	20.50	26.00	26.00	99.00
50 X 32	49.45	31.50	23.50	18.00	26.00	26.00	99.00
50 X 25	49.45	24.50	23.50	16.00	26.00	26.00	99.00
50 X 20	49.45	19.50	23.50	14.50	26.00	26.00	99.00
63 X 50	62.50	49.45	27.50	23.50	32.50	32.50	120.00
63 X 40	62.50	39.45	27.50	20.50	32.50	32.50	120.00
63 X 32	62.50	31.50	27.50	18.00	32.50	32.50	120.00
63 X 25	62.50	24.50	27.50	16.00	32.50	32.50	120.00
63 X 20	62.50	19.50	27.50	14.50	32.50	32.50	120.00
75 X 63	74.90	62.50	30.00	27.50	38.50	38.50	137.00
75 X 50	74.90	49.45	30.00	23.50	38.50	38.50	137.00
75 X 40	74.90	39.50	30.00	20.50	38.50	38.50	137.00
75 X 32	74.90	31.50	30.00	23.50	38.50	18.00	100.00
75 X 25	74.90	24.50	30.00	23.50	38.50	18.00	100.00
90 X 75	89.90	74.90	33.00	30.00	46.00	46.00	158.00
90 X 63	89.90	62.50	33.00	27.50	46.00	46.00	158.00
90 X 50	89.90	49.45	33.00	23.50	46.00	46.00	158.00
90 X 40	89.90	39.50	33.00	20.50	46.00	46.00	158.00
110 X 90	110.00	89.90	37.00	33.00	56.00	60.00	186.00
110 X 75	110.00	74.90	37.00	30.00	56.00	63.00	186.00
110 X 63	110.00	62.50	37.00	27.50	56.00	56.00	186.00
110 X 50	110.00	49.45	37.00	23.50	56.00	60.05	186.00
110 X 40	110.00	39.45	37.00	20.50	56.00	63.05	186.00
160 X 110	159.00	109.00	48.00	37.00	56.00	24.00	186.00








## **FOUR WAY TEE**

Size (mm)	ØD	W	Н
20	19.50	14.50	11.00
25	24.50	16.00	13.50
32	31.50	18.00	17.00












## **PLAIN UNION**

Size (mm)	ØD	L	Н	W
20	19.50	14.50	47.00	48.00
25	24.50	16.00	50.00	55.00
32	31.50	18.00	49.50	67.50
40	39.45	20.50	79.00	77.30
50	49.45	23.50	100.30	90.50
63	62.50	27.50	84.00	125.00








## **END CAP**

Size (mm)	ØD	L
20	19.50	14.50
25	24.50	16.00
32	31.50	18.00
40	39.45	20.50
50	49.45	23.50
63	62.50	27.50
75	74.90	30.00
90	89.90	33.00
110	110.00	37.00
160	159.00	48.00








## **END PLUG**


Size (mm)	Threads	Н
20	1/2	22.50
25	3/4	25.00
32	1	28.00








# **EXTENDED END PLUG**









## **CROSS OVER**

### (MOULDED)

Size (mm)	ØD	L	н	Т
25	24.50	200.24	59.5	33.68
32	31.50	250.76	72.8	39.66



### (FABRICATED)


Size (mm)	ØD	W	L
20	20.00	55.00	390.00
25	25.00	56.00	400.00
32	32.00	72.00	450.00





## PIPE CLAMP

Size (mm)	ØD	Н	L	Z
20	20.50	27.00	40.00	19.25
25	25.50	31.00	39.00	21.75
32	32.50	37.00	48.00	25.25












## **GATE VALVE**

Size (mm)	ØD	L	Lτ
20	19.50	14.50	61.00
25	24.50	16.00	70.00
32	31.50	18.00	85.00
40	39.50	20.50	95.00
50	49.50	23.50	114.00
63	62.50	27.50	133.50








## **BALL VALVE**

### (HOT & COLD WATER)

Size (mm)	ØD	L	Н
20	19.50	73.04	62.24
25	24.50	77.60	74.26
32	31.50	87.64	86.42
40	39.45	103.72	98.36
50	49.45	123.92	116.86
63	62.50	149.36	139.10








## **FLANGE**

Size (mm)	ØD1	ØD2	ØD3	P.C.D	ØF	No. of Hole	Т
32	43.00	54.00	117.00	80.00	17.00	04	21.00
40	51.50	60.50	130.00	89.00	17.00	04	21.50
50	63.50	73.50	143.50	98.00	17.50	04	22.40
63	80.50	90.00	159.00	121.00	17.50	04	25.60
75	93.50	106.50	175.00	140.00	17.50	04	27.50
90	113.00	126.00	198.50	152.00	17.50	08	30.50
110	134.20	147.00	220.00	190.00	17.50	80	31.50
160	187.00	209.50	289.00	241.00	19.05	08	36.50








## FLANGE WITH CORE

Size (mm)	ØD	ØD1	L	Н	Т
32	31.50	53.00	20.00	22.50	8.00
40	39.45	59.50	22.30	29.30	12.00
50	49.45	72.50	24.10	30.00	12.00
63	62.50	88.00	27.50	32.00	12.00
75	74.90	104.50	30.00	35.50	14.00
90	89.90	124.00	33.00	38.00	16.00
110	110.00	145.00	37.00	44.50	16.00
160	156.00	205.50	48.60	58.50	19.40








## **REDUCER**

Size (mm)	ØD1	ØD2	L1	L2	Н
25 X 20	24.50	19.50	16.00	14.50	34.50
32 X 25	31.50	24.50	18.00	16.00	38.00
32 X 20	31.50	19.50	18.00	14.50	36.50
40 X 32	39.45	31.50	20.50	18.00	42.50
40 X 25	39.45	24.50	20.50	16.00	40.50
40 X 20	39.45	19.50	20.50	14.50	39.00
50 X 40	49.45	39.45	23.50	20.50	48.00
50 X 32	49.45	31.50	23.50	18.00	45.50
50 X 25	49.45	24.50	23.50	16.00	43.50
50 X 20	49.45	19.50	23.50	14.50	42.00
63 X 50	62.50	49.45	27.50	23.50	59.00
63 X 40	62.50	39.45	27.50	20.50	56.00
63 X 32	62.50	31.50	27.50	18.00	54.50
63 X 25	62.50	24.50	27.50	16.00	51.50
63 X 20	62.50	19.50	27.50	14.50	51.50
75 X 63	74.90	62.50	30.00	27.50	57.50
75 X 50	74.90	49.45	30.00	23.50	53.50
75 X 40	74.90	39.50	30.00	20.50	50.50
75 X 32	74.90	31.50	30.00	18.00	48.00
90 X 75	74.90	24.50	33.00	31.50	64.50
90 X 63	89.90	74.50	33.00	20.50	53.50
90 X 50	89.90	62.50	33.00	23.50	56.50
110 X 90	89.90	49.50	37.00	33.00	70.00
110 X 75	89.90	39.50	37.00	31.50	68.50
110 X 63	110.90	89.90	37.00	30.00	67.00
160 X 110	159.50	109.00	48.00	37.00	85.00













# TANK CONNECTOR SHORT










## **TANK CONNECTOR**

Size (mm)	ØD	L1	Lt	L2
20	20.00	140.00	66.00	20.00
25	25.00	146.00	72.00	22.00
32	32.00	150.00	76.00	25.00
40	40.00	166.00	91.00	29.00
50	50.00	180.00	105.00	35.00
63	63.00	198.00	123.00	42.00








## **STUB END**

Size (mm)	ØD	ØD1	L	Н	Т
32	31.50	59.00	20.00	22.50	8.00
40	39.45	68.00	22.30	29.30	12.00
50	49.45	76.50	24.10	30.00	12.00
63	62.50	99.50	27.50	32.00	12.00
75	74.90	118.50	30.00	35.50	14.00
90	89.90	130.50	33.00	38.00	16.00
110	110.00	168.50	37.00	44.50	16.00
160	156.00	218.00	48.60	58.50	19.40








### **SADDLE**

Size (mm)	ØD	ØD1	ØD2	L	Н
63 X 32	31.50	21.50	48.00	21.50	43.00
75 X 32	31.50	21.50	48.00	21.50	42.00
90 X 32	31.50	21.50	48.00	21.50	42.00
110 X 32	31.50	21.50	48.00	21.50	42.00
160 X 32	31.50	21.50	48.00	21.50	42.00



## **BRASS INSERT FITTINGS DIMENSIONS**






# MALE THREADED ADAPTOR

Size (mm)	ØD	Threads (inch)	L	Lτ	Н
20 X 20 (1/2")	19.50	1/2	14.50	15.00	54.50
25 X 25 (3/4")	24.50	3/4	16.00	17.00	58.00
32 X 32 (1")	31.50	1	18.00	19.00	62.00
40 X 40 (1 1/4")	39.45	1 1/4	20.50	22.00	72.00
50 X 50 (1 1/2")	49.45	1 1/2	23.50	22.00	75.00
63 X 63 (2")	62.50	2	27.50	26.30	88.30






### **REDUCING MALE THREADED ADAPTOR**

Size (mm)	ØD	Threads (inch)	L	Lт	Н
20 X 25 (3/4")	19.50	3/4	14.50	17.00	58.00
25 X 20 (1/2")	24.50	1/2	16.00	15.00	56.00
32 X 20 (1/2")	31.50	1/2	18.00	15.00	58.00
32 X 25 (3/4")	31.50	3/4	18.00	17.00	60.00
40 X 50 (1 1/2")	39.45	1 1/2	20.50	22.00	72.00

Refer Figure - 1

Size (mm)	Size (mm) ØD		L	Lτ	Н	
40 X 32 (1")	39.50	1	20.50	19.00	66.50	

Refer Figure - 2












## **FEMALE THREADED ADAPTOR**

Size (mm)	ØD	Threads (inch)	L	Lτ	Н
20 X 20 (1/2")	19.50	1/2	14.50	15.00	39.50
25 X 25 (3/4")	24.50	3/4	16.00	16.30	41.00
32 X 32 (1")	31.50	1	18.00	19.00	43.00
40 X 40 (1 1/4")	39.50	1 1/4	20.50	25.00	50.00
50 X 50 (1 1/2")	49.45	1 1/2	23.50	21.40	53.00
63 X 63 (2")	62.50	2	27.50	25.70	62.00




### REDUCING FEMALE THREADED ADAPTOR

Refer Figure - 1

Size (mm)	ØD	Threads (inch)	L	Lτ	Н
20 X 25 (3/4")	19.50	3/4	14.50	16.30	41.00
25 X 20 (1/2")	24.50	1/2	16.00	15.00	41.00
32 X 20 (1/2")	31.05	1/2	18.00	15.00	42.00
32 X 25 (3/4")	31.50	3/4	18.00	16.30	43.00

Refer Figure - 1

Size (mm)	ØD Threads (inch)		L	Lτ	Н
40 X 32 (1")	39.50	1	20.50	19.00	47.50
					Refer Figure - 2








## **MALE THREADED ELBOW**

Size (mm)	ØD	Threads (inch)	L	Lτ
20 X 20 (1/2")	19.50	1/2	14.50	15.00
25 X 25 (3/4")	24.50	3/4	16.00	17.00
32 X 32 (1")	31.50	1	18.00	19.00
40 X 40 (1 1/4")	39.45	1 1/4	20.50	22.00



### **REDUCING MALE THREADED ELBOW**

Size (mm)	ØD	Threads (inch)	L	Lτ
20 X 25 (3/4")	19.50	3/4	14.50	17.00
25 X 20 (1/2")	24.50	1/2	16.00	15.00
32 X 20 (1/2")	31.50	1/2	18.00	15.00
32 X 25 (3/4")	31.50	3/4	76.60	17.00






Size (mm)	ØD	Threads (inch)	L	LT
20 X 20 (1/2")	19.50	1/2	14.50	15.00
25 X 25 (3/4")	24.50	3/4	16.00	16.30
32 X 32 (1")	31.50	1	18.00	19.00
40 X 40 (1 1/4")	39.45	1 1/4	20.50	21.40

### **REDUCING FEMALE THREADED ELBOW**

Size (mm)	ØD	Threads (inch)	L	LT
20 X 25 (3/4")	19.50	3/4	14.50	16.00
25 X 20 (1/2")	24.50	1/2	16.00	15.00
32 X 20 (1/2")	31.50	1/2	18.00	15.00
32 X 25 (3/4")	31.50	3/4	59.60	16.00









## **FEMALE THREADED ELBOW WITH SUPPORT**

Size (mm)	ØD	Threads (inch)	L	LT	X1	X2	Ø
20 X 20 (1/2")	19.50	1/2	14.50	15.00	60.00	50.00	5.00



### REDUCING FEMALE THREADED ELBOW WITH SUPPORT

Size (mm)	ØD	Threads (inch)	L	LT	X1	X2	Ø
25 X 20 (1/2")	24.50	1/2	16.00	15.00	64.00	54.00	5.00
25 X 25 (3/4")	24.50	3/4	16.00	16.30	64.00	54.00	5.00












## MALE THREADED TEE

Size (mm)	ØD	Threads (inch)	L	Lτ	Н
20 X 20 (1/2")	19.50	1/2	14.50	15.00	51.00
25 X 25 (3/4")	24.50	3/4	16.00	17.00	59.00
32 X 32 (1")	31.50	1	18.00	19.00	70.00

### **REDUCING MALE THREADED TEE**

Size (mm)	ØD	Threads (inch)	L	Lт	Н
25 X 20 (1/2")	24.50	1/2	16.00	15.00	59.00
32 X 20 (1/2")	31.50	1/2	18.00	15.00	70.00
32 X 25 (3/4")	31.50	3/4	18.00	17.00	70.00








# FEMALE THREADED TEE

Size (mm)	ØD	Threads (inch)	L	Lτ	н
20 X 20 (1/2")	19.50	1/2	14.50	15.00	51.00
25 X 25 (3/4")	24.50	3/4	16.00	16.30	59.00
32 X 32 (1")	31.50	1	18.00	19.00	70.00



### REDUCING FEMALE THREADED TEE


Size (mm)	ØD	Threads (inch)	L	Lт	Н
25 X 20 (1/2")	24.50	1/2	16.00	15.00	59.00
32 X 20 (1/2")	31.50	1/2	18.00	15.00	70.00
32 X 25 (3/4")	31.50	3/4	18.00	16.30	70.00





# MALE THREADED UNION

Size (mm)	ØD	Threads (inch)	L
20 X 20 (1/2")	19.50	1/2"	14.50
25 X 25 (3/4")	24.50	3/4"	16.00
32 X 32 (1")	31.50	1"	18.00
40 X 40 (1 1/4")	39.50	1 1/4	20.50
50 X 50 (1 1/2")	49.50	1 1/2	23.50
63 X 63 (2")	62.50	2	27.50








# FEMALE THREADED UNION

Size (mm)	ØD	Threads (inch)	L	Lτ
20 X 20 (1/2")	19.50	1/2"	14.50	15.00
25 X 25 (3/4")	24.50	3/4"	16.00	16.30
32 X 32 (1")	31.50	1"	18.00	19.00
40 X 40 (1 1/4")	39.45	1 1/4"	20.50	21.40
50 X 50 (1 1/2")	49.45	1 1/2"	23.50	21.40
63 X 63 (2")	62.50	2"	27.50	25.70




## **WALL MIXER**



HOT DOWN & COLD DOWN

25mm (3/4") X 20mm (1/2")

Size (mm)	Size (inch)
160	6






HOT UP & COLD UP

25mm (3/4") X 20mm (1/2")

Size (mm)	Size (inch)
160	6






## HOT SIDE & COLD SIDE

25mm (3/4") X 20mm (1/2")

Size (mm)	Size (inch)
160	6






## HOT SIDE & COLD DOWN

25mm (3/4") X 20mm (1/2")

Size (mm)	Size (inch)
160	6










### **HOT DOWN & COLD SIDE**

25mm (3/4") X 20mm (1/2")

Size (mm)	Size (inch)
160	6






### **HOT UP & COLD DOWN**

25mm (3/4") X 20mm (1/2")

Size (mm)	Size (inch)
160	6






### **HOT DOWN & COLD UP**

25mm (3/4") X 20mm (1/2")

Size (mm)	Size (inch)			
160	6			



## **ACCESSORIES**



### **DIE SET**

Size (mm)	
20	
25	
32	
40	
50	
63	



### **CUTTER**

Size (mm)			
20 - 40			
50 - 90			
75 - 110			
160			

### **WELDING DEVICE**





### **REPAIR SECTION**



Size (mm) 7 X 11

# **REPAIR BAR**

Size (mm) 7 X 11

### **LARGE DIAMETER WELDING DEVICE**



Size (mm) 75 - 160 160

## **QUALITY ASSURANCE TESTS**

### **PIPES QUALITY TEST**

ACCEPTANCE TEST				
Visual Appearance				
Colour				
Dimensions				
Internal Long term Hydrostatic Pressure Test				
Heat Reversion				
Charpy Impact Strength				
Density				
Melt Flow Rate				
Carbon black content & dispersion (black pipes)				

### **FITTING QUALITY TEST**

ACCEPTANCE TEST					
Visual Appearance					
Colour					
Dimensions					
Wrenching test (insert & threaded items)					
Hammer Test					
Internal Hydrostatic pressure test					
Leakage test (insert items,extended end plug & tank connector)					

TYPE TEST	
Water hammer test	
Hot & cold water test	
Long term Hydrostatic Pressure test	

### **BALL VALVE QUALITY TEST**

ACCEPTANCE TEST
Visual Appearance
Colour
Dimensions
Internal Hydrostatic pressure test
Drip proofness test
Torque wrench test
Tumbler test

TYPE TEST
Endurance test
Long term Hydrostatic Pressure test



### **TECHNICAL DETAILS**

### THERMAL EXPANSION

A pipe line which is subjected to a variation of temperatures changes its length if it is free to do so, This change in length is proportional to the linear coefficient of thermal expansion of the material of pipeline. The linear expansion or contraction caused by the change in ambient temperature gradient can easily be calculated using the following formula.

 $\Delta L = \sigma X L X \Delta T$ 

WHERE:

 $\Delta L = Expansion(+) \text{ or contraction(-) in length,( mm)}$ 

L = Initial pipe length, (Meter)

 $\sigma$  = Coefficient of thermal expansion ( for PP-R = 0.15 mm/m°C)

 $\Delta T$  = Change in temperature (°C)

**EXAMPLE:** for 5 meter PP-R line operating between 25 to 55°C

 $\Delta T = (55-25)=30^{\circ}C$ 

 $\Delta L = 0.15 \text{ X } 5 \text{ X } 30 = 22.5 \text{ mm}$ 

The expansion and contraction adjustment of GREENFIT PP-R pipeline is generally made in longitudinal direction only. Enough space shall be provided and proper type of supports shall be used to allow the free movement of pipe in axial directions.

Once the change in length of pipeline on account of thermal expansion/contraction has been calculated, a correct planning of pipelines is necessary to ensure that its effect do not cause deformation of the piping itself. GREENFIT PP-R systems make it possible to easy and convenient compensation for change in length using the suitable provision of following:


- Fixed & Sliding supports.
- Free flexible pipe segment (Expansion Arm).
- Free flexible pipe loop (Compensation Loop).


### FREE AND SLIDING SUPPORTS


Fixed and Sliding supports secure external pipelines to the masonry structure of the building, to prevent the movements generated by thermal expansion, totally or partially.

**Fixed Supports:** - These are used when the axial expansion of the pipeline should be limited. Fixed support provides a rigid connection between external pipeline installations with masonry structure. The fixed supports must normally be positioned where the system changes direction


(Elbows, Tees, etc.) & near to Valves, Cocks, Water meter, etc. to ensure that expansion forces are not induced these points. In all cases, fixed support should always be provided next to any joint in the pipeline created using any welded fitting. Obviously the fixed supports limit the length of section of pipe free to expand, and reduce the relative change in length value.







**Sliding Supports:** - are used to allow the pipe to move axially in both directions. They have to be positioned well away from joints made using welded fittings, on a free length of the pipes surface. The sliding support collar must be absolutely free from pipe diameter otherwise it may damage the surface of the pipe where it is installed. Sliding support also ensures that the pipeline remain straight in spite of thermal stresses.




**Support Spacing: -** For horizontal and vertical external pipeline installation on wall, the recommended distances between supports are given in following tables for various pipe sizes.

Size	Horizontal clamp spacing distance according to temperatures, cm				to		
(mm)	20°C 30°C		40°C	50°C	60°C	70°C	80°C
20	65	63	61	60	58	53	48
25	75	74	70	698	66	61	56
32	90	88	86	83	80	75	70
40	110	110	105	100	95	90	85
50	125	120	115	110	105	100	90
63	140	135	130	125	120	115	105
75	155	150	145	135	130	125	115
90	165	160	155	145	140	130	120
110	175	175	170	165	155	145	135

Size	Horizontal clamp spacing distance according to temperatures, cm				to		
(mm)	20°C	30°C	40°C	50°C	60°C	70°C	80°C
20	85	82	79	78	75	69	62
25	98	96	91	88	86	79	73
32	117	114	112	108	104	98	91
40	143	143	137	130	124	117	111
50	163	156	150	143	137	130	117
63	182	176	169	163	156	150	137
75	202	195	189	176	169	163	150
90	215	208	202	189	182	169	156
110	228	228	221	215	202	189	176

### FREE FLEXIBLE PIPE SEGMENT (EXPANSION ARM)

With the help of free flexible pipe segment, provided at the position of change in direction, the change in length of pipeline is totally compensated. The length of free flexible pipe segment is calculated using following formula:



LS = CÖdxDL where

LS = Length of free flexible segment (mm).

C = Constant of material (for PP-R, C= 30).

d = Pipe outside diameter (mm).

 $\Delta L$  = Expansion or contraction length (mm).







### FREE FLEXIBLE PIPE LOOP (COMPENSATION LOOP)

If the change in length cannot be compensated using expansion arm, it is necessary to install a free flexible loop (Compensation loop). Free flexible bend can be easily prepared on site with required lengths of GREENFIT PP-R pipe & 4 nos. of 90 ° elbows.

To prepare a free flexible loop you have to calculate:



- The length of free flexible segment (LS) with the help of formula as explained in Free flexible pipe segment (Expansion Arm)
- The minimum width (B) between two arms of the loop = 10 times the outside diameter of the pipe.



### LAYING IN SANITARY SHAFT / PIPE DUCT OF A BUILDING

No.	Recommendation For Pipe Connection	Description		
1	LS	Pipe connection can be made At some distance away from The wall		
2		The connecting pipe can be Passed through a hole much Larger than the pipe diameter		
3		The connection can  Be made through a  Branch pipe to provide flexibility		

When making the apartment pipe connections from main pipe going through the sanitary shaft of the building, the alternative techniques shown above can be applied in order to compensate for thermal expansion & contraction.

### **BENDING**

During laying of pipeline, GREENFIT PP-R pipes may be required to be bent. Bending shall be done by using hot air blowing at 140°C. Direct heating by open flame shall be avoided, Radius for GREENFIT PP-R pipe bend should be minimum 8 times its diameter. The table given besides indicate minimum bending radius for each sized of pipe.

Drawing	Pipe diameter (mm)	Minimum bending radius (mm)
	20	160
R	25	200
	32	256
	40	320
	50	400

### **INSULATION FOR LOWER TEMPERATURE**

#### **FOR HOT WATER**

When conveying hot water through any pipe, heat is transferred through the pipe wall. PRINCE pipes have a much lower GREENFIT PP-R coefficient of thermal conductivity (0.24 W / mK) compared to metal pipes. Therefore, normally it may not be required to insulate the pipelines which is used for hot water concealed application. However, for centralised heating systems, to prevent heat loss and isolate the pipelines from other utilities, it is advisable to insulate these lines. The required thickness of insulation is quite lower as compared with conventional lines. Given besides are the recommended insulation thickness for different pipe size.

Div - Oi	Thermal conductivity of insulation material		
Pipe Size (mm)	0.030 W /m.K	0.030 W /m.K	
	Recommended minimum insulation thickness in mm		
20	6	10	
25	6	10	
32	10	13	
40	10	13	
50	10	13	
63	13	20	
75	20	20	
90	20	25	
110	25	32	

#### FOR COLD WATER

Potable cold water plants have to be protected against heat gain and the formation of condensation. Standard value for the minimum thickness of insulation as stipulated in DIN-1988, part 2 have to be taken from the following table:

Minimum insulation thickness for the insulation of potable water pipes (10°C) as per DIN 1988, part 2			
Type of installation	Insulation thickness (for 0.04 W/m.K thermal conductivity material) in mm		
Open installed pipes, in non heated room (I.e. celler)	4mm		
Open installed pipe in heated room	9mm		
Pipe in a duct, without warm pipe	4mm		
Pipe in a duct beside warm pipe	13mm		
Pipe in a pipe chase riser	4mm		
Pipe in a pipe chase, beside warm water pipes	13mm		
Pipe on concrete floor	4mm		

### **RESISTANCE TO ULTRA VIOLET (UV) RAYS**

PRINCE monolayer pipes & fittings are have sufficient U.V. stability in order to protect them GREENFIT PP-R from UV rays during storage in open area for a period of about 6 months. However, it is not advisable to use these pipes and fittings under direct sunlight continuously. For outdoor installation on pipelines, PRINCE Piping Systems offers 3 layers GREENFIT PP-R pipes, which are resistant to U.V. rays.

### **SUITABILITY FOR DRINKING WATER**

PRINCE pipes & fittings meet the requirements of IS 10500-91 for drinking water and GREENFIT PP-R IS 10146-87 for leachable additives as its safe use for drinking water.

### **FIRE RESISTANCE**

PRINCE pipes & fittings have combustion point 330°C & burning point 360°C. These conform GREENFIT PP-R with B2 class fire requirements of normal combustibility according to DIN 4102. On fire, PP-R pipes & fittings emit carbon dioxide and water. Other than this, carbon monoxide gas, molecular hydrocarbon and oxidation products of these are also emitted in proportion to the availability of oxygen. Even if the fire is incomplete, the materials emitted are less poisonous than wood or similar materials on fire under the same conditions. The smoke that comes out of GREENFIT PP-R fire does not cause rusting.

### LOW TEMPERATURE RESISTANCE

At lower temperature of 0° C and below, the flexibility of pipes reduces and impact strength GREENFIT PP-R also reduces. This makes pipes more prone to mechanical damages against impact loads. To avoid the damages at low temperature, it is advisable to insulate the pipe lines.



### **DESIGN GUIDELINES**

### **GENERAL GUIDELINES**

While designing the GREENFIT PP-R piping system, one should be aware that GREENFIT PP-R piping is quiet different than other traditional materials like GI or Copper as well as PVC or CPVC. For good and safe design an installation, the following shall be taken into account.

- Pipes & fittings have different dimensions from other types of pipes and fittings. Even though the bore diameter of pipe is less than the
  equivalent metal or plastic pipe, the flow is more due to smoothness & less friction. Hydraulic calculation should be done each time for
  the best choice of pipeline diameters.
- Linear thermal expansion/contraction of GREENFIT PP-R pipes is more as compared with metal pipes. This needs to be taken care
  during designing and installation to avoid stressing of pipeline by providing flexible free length and proper supporting.
  (Refer page no. 28 Thermal expansion)
- STANDARD WORKING CONDITION AND SERVICE LIFE for designing (Refer page no. 7)
- · Use 3 layer pipes for outdoor installations.
- · Use Black pipes for solar heating system.
- Provide insulation for centralized heating systems and chilled water systems. (Refer page no.31- Insulation)
- Dos & Don'ts (Refer page no. 35 to 36)

### **PIPELINE DESIGN**

#### **FLOW RATE**

Analytical flow is typical for each analytical section. Draw-off point's water quantity shall be worked out, taking into consideration water consumption (which is not simultaneous at all draw-offs). Following table gives formula for calculating the analytical flow for the different types of application:

Amelianting	Design flow rate Q, in Ips as per DIN 1988 part 3 can be calculated from following formula		
Application	formula for 0.07<Σq<20lps	formula for Sq>20lps	
Residential buildings	Q=0.682 (Σq) <sup>0.45</sup> -0.14	Q=1.7(Σq) <sup>0.21</sup> -0.7	
Commercial buildings	Q=0.682 (Σq) <sup>0.45</sup> -0.14	Q=1.4(Σq) <sup>0.54</sup> -0.48	
Hotels & Shoping Malls	Q=0.4 (Σq) <sup>0.366</sup> Q=0.698 (Σq) <sup>0.5</sup> -0.12	Q=1.08(Σq) $^{0.5}$ -1.82 Q=1.08(Σq) $^{0.5}$ -0.12	
Hospitals	Q=0.698 (Σq) <sup>0.5</sup> -0.12	Q=0.25(Σq) <sup>0.65</sup> -1.25	
Schools	Q=4.4 (Σq) <sup>0.27</sup> -3.41	Q=22.5 (Σq) <sup>0.5</sup> -11.5	

WHERE: Q = Standard outflow from the draw-off points, Ips

 $\Sigma q = Sum \text{ of all standard outflows from the draw-off points serviced by dimensional section of the installation , lps$ 

### **DESIGN FLOW RATES OF COMMON WATER POINTS**

	Type of water point	Calculated Flow on Taking		
Minimum Pressure		Mixed water	Only Cold or Warm Potable Water	
		Cold / Warm		
Bar	Designation	lps	Ips	
0.5	Taps Without air inlet DN 15	-	0.30	
0.5	Taps Without air inlet DN 20	-	0.50	
0.5	Taps Without air inlet DN 25	-	1.00	
1.0	Taps With air inlet DN 10	-	0.15	
1.0	Taps With air inlet DN 15	-	0.15	
1.0	Shower heads for purification showers DN15	0.10	0.20	
1.2	Flush Valves DN 15 (Toilet)	-	0.70	
0.4	F.V. DN 25 (Toilet)	-	1.00	
1.0	Flush Valves DN 15 (Urinal)	-	0.30	
1.0	Domestic dish washers DN 15	-	0.15	
1.0	Domestic washing machine DN 15	-	0.25	

#### **DESIGN FLOW RATES OF COMMON WATER POINTS**

Bar   Do   M		Calculated FI	ow on Taking
7	Type of water point	Mixed Water	Only Cold or Warm Potable
1 1000010		Cold/Warm	Water
Bar	Designation	lps	Ips
	Mixing battery for :		
1.0	Shower-bathes DN15	0.15	-
1.0	Bath-tubs DN15	0.15	-
1.0	Kitchen sinks DN 15	0.07	-
1.0	Washstands DN 15	0.07	-
1.0	Bidet DN 15	0.07	-
1.0	Mixing battery DN2O	0.30	-
0.5	Geyser DN 30	-	0.15
1.0	Geyser DN 20	-	0.20

### PRESSURE LOSS

In normal piping, two types of pressure loss can be found,

- 1. Distributed pressure loss related to pipe roughness, dimensions, physical properties and velocity of the liquids.
- 2. Local loss related to elbows, tees, valves and fittings which cause a remarkable variation in the liquid flow.

#### 1. DISTRIBUTED PRESSURE LOSS

The GREENFIT PP-R pipe has extremely smooth inner surfaces compared to metal pipes. Therefore, pressure loss is quiet low.

#### 2. LOCAL PRESSURE LOSS

In pipeline, local pressure loss takes place due to presence of fittings which can be calculated using following formula

$$R = \frac{(r) V^2 \sigma}{2 g}$$

WHERE: R = Total local pressure loss in (mm)

r = Local resistance coefficient value as given in following table

V = Mean velocity of fluid in (m/s)

g = Acceleration of gravity = 9.81 (m/s<sup>2</sup>)

 $\sigma$  = Specific gravity of water = 1000 (kq/m<sup>3</sup>)

Local resistance coefficient "r" for PRINCE GREENFIT PP-R plumbing fittings.

#### Note:

- These are reference values and they vary according to water temperature.
- As fitting diameter increases, the value of 'r' decreases.

Name of PP-R Fitting	Symbol for PP-R Fitting	Coefficient Value (r)
Coupler	<u> </u>	0.25
Reducer: Single stage reducer Double stage reducer Three stage reducer Four stage reducer	*	0.50 0.60 0.70 0.85
Elbow 90° Elbow 45°		1.2 0.5
Tee	<b>→ † →</b>	1.8
Male / Female Threaded Tee	_ <b>__↑↑</b>	1.8
Reducing Tee	<b>→ ↑</b>	3.0
Male / Female Threaded Adaptor Reducing Male / Female Adaptor		0.5 0.8
Male / Female Threaded adaptor Reducing Threaded Elbow adaptor		1.4 1.6
Valve 20 25 32		9.5 8.5 7.6
Union	→ →	8.3



### JOINTING METHODS

#### **PROCESS:** Fusion Welding

#### **CUTTING**

- · Cut the pipe at a right angle to its axis using burr-free cutter.
- Ensure that the pipe is free from burrs or cutting chips.
- Clean the pipe & fitting perfectly before welding.
- · Mark welding depth at the end of pipe.





#### **HEATING**

- Mount the suitable dyes on the heating element of the welding machine according to the diameter of pipe and fitting.
- Connect the welding machine to 220 volts A.C. power supply.
- Select 260°C temperature on the welding machine thermostat.
- · Wait until the required working temperature is reached.
- Insert the pipe and the fitting in the dyes by exerting light pressure.





#### **WELDING**

- After heating, quickly insert the pipe into the fitting by exerting light pressure.
- Any misalignment should be corrected immediately after insertion to avoid any stress in the weld.
- · Allow the joint to cool as per the cooling time given in table.

### **DON'Ts**



#### **CUTTING**

Do not cut slant/unevenly.



#### **DEBURRING AND RIDGE REMOVAL**

Do not proceed with installation of pipe without deburring as the burr when heated will create an extra blockage inside the pipe.



#### **CLEANING & MARKING**

Do not proceed without cleaning as it will create problems during welding due to the presence of dirt or mud.

#### **WELDING JOINT**

- Do not set the temperature of the heater higher or lower than 260°C
- · Do not initiate the jointing process without gloves.
- Misalignment of jointing to be corrected immediately before cooling, so as to avoid stress in the weld.




### **DOs**



#### **STORAGE**


Although Greenfit PP-R Pipe system material is stabilized for use at elevated temperatures do not expose the pipes & fittings to direct sunlight.



#### **STORAGE**


**DON'Ts** 

Greenfit PP-R Pipe storage height should not be more than 1.5 meter.



#### **TRANSPORTATION**

During transportation, Greenfit PP-R pipes should be loaded in a proper manner, otherwise pipes may get deformed.




#### **HANDLING**

The Greenfit PP-R Pipe system should be protected from impact of hard and sharp objects.



#### PREPARATION FOR WELDING

Before welding/jointing, clean the surface of Greenfit PP-R Pipes & Fittings with a clean piece of cloth and then start welding.



#### **HEATING**

While welding of Greenfit PP-R Pipes and fittings check that the thermostat of welding machine and dyes have reached correct temperature (260°C). While welding, the pipe must not be twisted.




#### **WELDING**

Avoid air droughts during welding to avoid stress in the welds.



#### **SAFE WELDING**

Welding machines shall be earthed properly during use.







### **DOs**



#### **SAFE WELDING**

Do not cool welding machine in water.



# **DON'Ts**




#### **THREAD JOINT**

Do not over tighten threaded fittings & valves.




#### **BENDING**

Do not apply direct flame to fabricate bends or crossover pipes, as the direct exposure to fire may cause damage to the Greenfit PP-R pipes. Use only hot air blowing equipment at 140°C. (Cross overs are readily available.)




#### **BENDING**

While bending the pipe, the bending radius shall be more than 8 times the diameter of the pipe.




#### **INSTALLATION AT LOWER TEMPERATURE**

At sub zero temperatures (0°C & below) Greenfit PP-R Pipe system tends to break under impact. Therefore, installation at low temperatures should be done with care, and the pipe lines shall be insulated.



#### **OUTDOOR INSTALLATION**

Use 3 layered pipes for outdoor application.



### RECOMMENDED TIME FOR PP-R FUSION JOINTS

Pipe Dia (mm)	Welding Depth (mm)	Heating Time (Sec)	Welding Time (Sec)	Cooling Time (Sec)
20	14.50	6	4	2
25	16.00	7	4	2
32	18.00	8	6	4
40	20.50	12	6	4
50	23.50	18	6	4
63	27.50	24	8	6
75	30.00	30	8	6
90	33.00	40	8	6
110	37.00	50	10	8
160	55.00	60	15	10

### **HOLE REPAIRING**


In case of accidental hole formation in pipe line due to drilling or piercing of pointed object, the pipe line can be repaired as follows:



Accidental hole formation in pipe line.



Simultaneously heat the hole section in the pipe line and repair bar using repair section die and welding device for about 5 to 7 seconds depending upon the pipe thickness.



Insert heated repair bar in the hole up till the full depth and hold it for a minute.



After cooling, cut the repair bar projected outside the pipe line using pipe cutter.

### **TESTING THE INSTALLATION**

#### PRESSURE TEST

According to DIN 1988 GREENFIT PP-R Pipeline for potable water installation have to be (before concealing) hydraulically pressure tested as described under While carrying out the pressure test the material properties of GREENFIT PP-R pipes lead to expansion of pipe.

This influences the test result. A further influence of the result can be caused by the thermal expansion of GREENFIT PP-R pipes. Different temperatures of pipe & test medium lead to alteration of pressure. (A temperature change of 10°C corresponds to pressure difference of 0.5 to 1 bar). Therefore, the highest possible constant temperature of the test medium has to be ascertained at the hydraulic pressure test of installations with GREENFIT PP-R pipes.

PRIMARY TEST	MAIN TEST
For primary test, a pressure of 1.5 times of rated pressure shall be applied for a duration of 30 minutes. During this test, pressure drop shall be < 0.6 bar.  If the pressure drops is > 0.6 bar, check the pipeline for leakage & retest.	After completion of primary test, main test must be conducted, which has to be effected with a test pressure of alternate1 bar & 10 bar for every 5 minutes interval for 2 hours.





Chemical	PVC					CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
A																
Acetaldehyde	N	N	N	N	N	N	N	N	N	N	_	_	-	_	-	-
Aqueous, 40%	С	N	_	_	_	-	-	-	R	R	R	С	N	-	-	-
Acetamide	R	_	_	R	_	-	_	-	R	-	_	_	-	R	-	-
Acetic Acid, 10%	R	R	С	R	R	R	R	R	R	R	R	R	R	R	-	-
Acetic Acid, 20%	R	R	С	R	R	R	R	R	R	R	R	R	R	R	-	-
Acetic Acid, 25%	R	R	С	R	R	R	R	R	R	R	R	R	R	R	-	-
Acetic Acid, 30%	R	С	С	R	-	С	-	-	R	R	R	R	R	R	-	-
Acetic Acid, 60%	R	С	С	R	-	С	-	-	R	R	R	R	С	R	-	-
Acetic Acid, 80%	R	С	С	R	-	-	-	С	R	N	N	N	N	R	-	-
Acetic Acid, 85%	R	-	-	N	-	-	-	-	R	-	-	-	-	R	-	-
Acetic Acid Glacial, 100%	С	N	N	С	N	N	N	N	R	С	С	-	N	R	-	-
Acetic Acid, Hot	-	-	-	-	-	-	-	-	-	-	-	-	-	_	-	-
Acetic Acid, Vapor	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Acetic Anhydride	N	-	-	-	-	-	-	-	R	С	С	-	N	R	-	-
Acetone	N	-	-	N	-	-	-	-	R	R	R	-	-	-	-	-
Acetone 5%	N	-	-	N	-	-	-	-	R	R	R	-	-	-	-	-
Acetone, pure	N	N	N	N	N	N	N	N	С	С	С	-	-	-	-	-
Acetone, up to 5%	-	-	-	R	-	-	-	-	-	-	-	-	-	-	-	-
Acetonitrile	-	-	-	-	-	-	-	-	R	-	-	-	-	-	-	-
Acetopheneditin	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Acetophenone	-	-	-	-	-	-	-	-	R	-	N	-	-	R	-	-
Acetyl Acetone	N	-	-	N	-	-	-	-	-	-	-	-	-	-	-	-
Acetyl Bromide	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Acetyl Chloride	N	-	-	N	-	-	-	-	R	-	-	-	-	-	-	-
Acetyl Nitrite	N	-	-	N	-	-	-	-	-	-	-	-	-	-	-	-
Acetyl-d I-Alanine	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Acetyl-d 1-Lencine-n	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Acetyl-d I-Meth ionine-n	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Acetyl-d 1-Trytophan-n	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Acetylene Gas, 100%	N	-	-	N	-	-	-	-	R	-	-	-	-	R	-	-
Acetylene Tetrabromide	-	-	-	-	-	-	-	-	-	-	-	-	-	N	-	-
Acetylnitrile	-	-	N	N	N	-	-	-	-	R	R	-	-	-	-	-
Acetylsalicylic Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-
Acetylonitrile	N	-	-	N	-	-	-	-	С	-	-	-	-	R	-	-
Adipic Acid, Sat'd	-	R	R	С	R	-	-	-	-	R	R	R	R	R	R	-
Aero Lubriplate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Alanine-dl	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Alcohols	R	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
Allyl Alcohol,96%	С	N	N	R	-	-	-	-	R	R	R	-	R	R	-	-
Allyl Chloride	N	-	-	N	-	-	-	-	-	-	-	-	-	-	-	-
Aloin	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-

 $<sup>\</sup>boldsymbol{R}$  - Stands for recommended |  $\boldsymbol{C}$  - Stands for use with caution |  $\boldsymbol{N}$  - Stands for not recommended

Chemical		PVC				CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Aluminum Acetate, Sat'd	R	-	-	R	-	-	-	-	R	-	-	_	-	R	-	-
Aluminum Ammonium	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Aluminum Bromide	R	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
Aluminum Chloride, Sat'd	R	R	R	R	-	R	-	-	R	R	R	R	С	R	-	-
Aluminum Fluoride, Sat'd	R	-	R	R	-	-	-	-	R	-	-	-	-	R	-	-
Aluminum Hydroxide, Sat'd	R	-	R	R	-	-	-	-	R	-	-	-	-	R	-	-
Aluminum Nitrate Sat'd	R	-	R	R	-	-	-	-	R	-	-	-	-	R	-	-
Aluminum Oxalate	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Aluminum Oxide	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-	-
Aluminum Oxychloride	R	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
Aluminum Potassium Sulfate, Sat'd	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Aluminum Salts	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Aluminum Sodium Sulfate	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-	-
Aluminum Sulfate, Sat'd	R	R	R	R	-	R	-	R	R	R	R	R	R	R	-	-
Alums, NH3-Cr-K	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ambrex 33 (Mobil)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ambrex 830 (Mobil)	-	-	-	-		-	-	-	-	-	-	-	-	-	-	-
Amines	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Amino Acetic Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Aminobutric-a-dl Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Aminoisobutyric-2 Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Ammonia Anhydrous	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Ammonia Gas 1	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-	-
Ammonia Gas, Cold	R	R	R	-	-	-	-	-	R	R	R	-	-	-	-	-
Ammonia Liquid 2	-	N	R	-	-	-	-	R	-	-	-	-	R	-	-	-
Ammonium Acetate, Sat'd 1	R	С	R	-	-	-	-	R	R	R	R	R	R	-	-	-
Ammonium Benzoate	-	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Ammonium Bifluoride, Sat'd	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Ammonium Bisulfide	R	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Bromide Ammonium Carbonate, Sat'd	R	R	С	R	-	-	-	-	R	R	R	R	R	R	-	-
Ammonium Chloride, Sat'd	R	-	R	R	-	R	-	R	R	-	R	-	С	R	R	R
Ammonium Citrate	-	-	-	R	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Dichromate	R	-	-	R	-	-	-	-	-	-	-	-	-	С	-	-
Ammonium	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Fluoride, 10%	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Ammonium Fluoride, 20%	R	-	С	R	-	R	-	-	R	-	R	-	-	-	-	-
Ammonium Fluoride, 25%	R	-	С	R	-	R	-	-	R	-	R	-	-	R	-	-
Ammonium Fluoro Silicate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Glycolate	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Ammonium Hydroxide	R	R	R	-	R	R	R	-	R	R	R	R	R	R	-	-
Ammonium 1	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-	-

In the table the figure stands for the below mentioned:



Chemical		PVC				CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Ammonium Molybdate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Nitrate, Sat'd	R	-	R	R	-	R	-	R	R	-	R	-	R	R	-	-
Ammonium Nitrite	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Oxalate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Oxylate	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	_
Ammonium Persulfate	R	-	R	R	-	-	-	-	R	-	-	-	-	R	-	-
Ammonium Persulfate,10%	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Phosphate, Dibasic	R	R	R	R	-	С	-	-	R	R	R	R	R	R	-	-
Ammonium Phosphate, Monobasic	R	R	R	R	-	-	-	-	R	R	R	R	R	R	-	_
Ammonium Phosphate	R	R	R	R	-	-	-	-	R	R	R	R	R	R	-	-
Ammonium Potassium	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Ammonium Sulfamate	-	-	-	R	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Sulfate	R	R	С	R	-	-	-	-	R	R	R	R	R	R	-	-
Ammonium Sulfide, Dilute	R	-	С	R	-	-	-	-	R	-	R	-	-	R	-	-
Ammonium Sulfocyanide f\mmonium Tartarate	-	-	-	R	-	-	-	-	-	-	-	-	-	-	-	-
Ammonium Thiocyanate	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Ammonium Thioglycolate	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Amonia Acetate, Sat'd	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Amonia Gas 1	-	-	N	-	-	-	-	R	-	-	-	-	R	-	-	-
Amonia Liquid 3	-	-	N	-	-	-	-	R	-	-	-	-	R	-	-	-
Amyl Acetate 3	-	N	N	-	N	-	-	С	С	-	-	-	R	-	-	-
Amyl Alcohol, Pure	R	R	С	R	-	R	-	R	R	R	R	R	R	R	-	-
Amyl Borate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Amyl Chloride 3	-	-	N	-	-	-	-	N	-	-	-	-	-	-	-	-
Amyl Chloronaphthalene	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Amyl Naphthalene	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Amyl Phthalate	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-	-
Ang-25 (Glyceral Ester)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Aniline 3	-	N	N	-	N	-	N	С	-	-	-	-	R	-	-	-
Aniline Chlorohydrate	С	-	N	N	-	N	-	N	С	-	С	-	N	-	-	-
Aniline Dyes	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Aniline Hydrochloride, Aniline Sulphate	R	С	-	N	-	-	-	-	R	R	С	-	-	R	-	-
Animal Oil	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Anthranilac Acid	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-	-
Anthraquinone 1	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-	-
Anthraquinone Sulfonic	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Antimony Trichloride	R	R	R	R	-	-	-	-	R	R	R	-	-	R	-	-
Aqua Regia 1	С	С	С	С	С	С	С	С	N	N	N	N	N	-	-	-
Arachidic Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Argon, Dry	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

 $<sup>\</sup>boldsymbol{R}$  - Stands for recommended |  $\boldsymbol{C}$  - Stands for use with caution |  $\boldsymbol{N}$  - Stands for not recommended

Chemical	PVC					CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Aromatic Fuel, 50%	-	_	-	-	-	-	-	-	-	_	-	-	-	-	-	-
Aromatic Hydrocarbons	N	-	-	N	_	-	-	-	_	-	-	-	-	-	-	_
Arsenic Acid, 80%	R	R	С	R	С	С	С	С	R	R	R	R	С	R	-	-
Arsenic Trioxide (Powder)	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Arylsulfonic Acid 1	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-	-
Ascorbic Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Askarel	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Asphalt 3	-	-	N	-	-	-	-	R	-	-	-	-	N	-	-	-
ASTM Oil, NO.1 1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
ASTM Oil, NO.2 1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
ASTM Oil, NO.3 1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Atropine Sulfate	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-	-
Aurex 903R (Mobile)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Automatic Transmission Automotive Brake Fluid	С	-	-	-	-	-	-	-	R	-	-	-	-	R	-	-
В																
Bardol B	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Barium Acetate Sat'd	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Barium Bromide	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Barium Carbonate, Sat'd	R	-	R	R	-	-	-	-	R	-	R	-	-	R	-	-
Barium Chloride, Sat'd	R	R	R	R	-	-	-	-	R	-	R	-	-	R	-	-
Barium Cyanide	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Barium Hydroxide,10%	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Barium Hydroxide, Sat'd	R	R	R	R	-	-	-	-	R	R	R	-	-	R	-	-
Barium Nitrate, Sat'd	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Barium Sulfate, Sat'd	R	R	R	R	-	-	-	-	R	-	R	-	-	R	-	-
Barium Sulfide, Sat'd	R	R	R	R	-	-	-	-	R	-	-	-	-	R	-	-
Bayol35	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Bayol D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Beer	R	R	R	R	-	-	-	-	R	R	R	-	-	R	-	-
Beet Sugar Liquors	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Benzal Chloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzaldehyde	N	-	N	N	-	-	-	-	N	-	N	-	-	N	-	-
Benzaldehyde, 1%	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzaldehyde, 10%	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Benzaldehyde, >10%	N	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzaldehyde, 10%	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Benzaldehyde, 5%	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Benzalkonium Chloride	R	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Benzamide	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzene	N	N	N	N	-	-	-	-	С	-	N	-	N	С	-	-
Benzene Sulfonic Acid, Sat'd	N	N	N	N	N	N	N	N	R	R	R	N	N	R	R	С

In the table the figure stands for the below mentioned:



Chemical	PVC				CPVC					PPR				HDPE		
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Benzene Sulfonic Acid,10%	N	N	N	N	N	N	N	N	R	С	N	-	-	N	-	-
Benzenesulfonic Acid	N	-	-	N	-	-	-	-	N	-	-	-	-	R	-	-
Benzenesulfonic Acid,10%	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Benzine	R	R	R	-	-	-	-	-	С	-	-	-	-	-	-	-
Benzochloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzoic Acid, All	R	R	С	R	-	С	-	-	R	R	R	R	R	R	-	-
Benzoic Acid Crystals	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzoic Sulfimide	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzophenone	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzotrichloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzotrifluoride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzoyl Benzoic Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzoyl Chloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzyl Acetate	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Benzyl Alcohol	С	-	-	R	-	-	-	-	R	R	С	-	-	R	-	-
Benzyl Alcohol,1,5%	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzyl Benzoate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Benzyl Chloride	-	-	-	-	R	-	-	-	-	-	-	-	-	-	-	-
Beryllium Sulfate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Bismuth Carbonate	R	-	-	-	R	-	-	-	R	-	-	-	-	R	-	-
Black Liquor	R	-	-	-	R	-	-	-	R	-	-	-	-	R	-	-
Black Point 77	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Blast Furnace Gas	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Bleach, 12% Active Ci2	-	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
Bleach, 5% Active Ci2	R	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
Bleach Liauor	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Blood	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Borax, Sat'd	R	R	С	R	-	-	-	-	R	R	R	R	R	R	-	-
Bordeaux Mixture	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Boric Acid, 10%	R	-	С	R	R	R	R	R	R	R	R	R	R	R	-	-
Boric Acid, Sat'd	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Boron Fluids (HEF)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Boron Trifluoride	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Brake Fluid	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Brine, Sat'd	R	R	R	R	-	R	-	-	R	R	R	R	R	-	-	-
Brom-113	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Brom-114	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Bromic Acid	R	-	-	R	-	-	-	-	N	-	-	-	-	-	-	-
Bromic Acid, 10%	R	-	R	R	-	R	-	R	-	-	-	-	-	-	-	-
Bromine, Aqueous	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Bromine Liquid	N	-	N	N	-	N	-	N	N	-	N	-	N	N	-	-
Bromine Pentafluoride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

 $<sup>\</sup>boldsymbol{R}$  - Stands for recommended |  $\boldsymbol{C}$  - Stands for use with caution |  $\boldsymbol{N}$  - Stands for not recommended

Chemical	PVC					CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Bromine Trifluoride	-	-	_	-	-	-	-	_	-	_	-	-	-	-	-	-
Bromine Vapor, 25%	R	_	_	R	-	-	_	_	N	_	_	_	-	R	-	_
Bromine Water cold, Sat'd	N	_	_	-	-	-	_	_	_	_	_	-	-	N	-	_
Bromoacetic Acid	-	_	_	_	-	-	_	-	_	_	_	-	-	_	-	_
Bromobenzene	-	-	-	-		-	-	-	-	-	-	-	-	N	-	-
Bromobutyric-2 Acid	-	-	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Bromochloro	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Bromoform	-	-	-	-	-	-	-	-	-	-	-	-	-	N	-	-
Bromosalicylic Acid, Sat'd	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-
Bromotoluene	N	-	-	-	-	-	-	-	-	-	-	-	-	N	-	-
Bunker Oil	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butadiene	R	-	R	R	-	-	-	-	R	R	R	-	-	_	-	-
Butadiene, 50%	R	-	-	R	-	-	-	-	N	-	-	-	-	R	-	-
Butadiene Gas	R	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
B utanane- 2, 4-p-Methoxy	-	-	-	-	-	-	-	-	-	_	-	-	-	N	-	-
Butane, 50%	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Butane, Gas	R	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
Butter - Animal Fat	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Acetate	N	-	N	N	-	N	-	N	С	-	-	-	-	-	-	-
Butyl Acetyl Ricinoleate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Acrylate Pure	N	-	-	N	-	-	-	-	N	-	-	-	-	-	-	-
Butyl Alcohol	R	-	С	R	R	-	-	-	R	-	R	-	С	R	-	-
Butyl Benzoate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Bromide	-	-	-	-	-	-	-	-	-	-	-	-	R	-	-	-
Butyl Butyrate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Carbitol	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Cellosolve	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Cellosolve"Adipate	-	-	-	N	-	-	-	-	-	-	-	-	-	N	-	-
Butyl Chloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Ether	N	-	-	N	-	-	-	-	N	-	-	-	-	-	-	-
Butyl Glycolate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Mercaptan	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Oleate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyl Pheno	С	-	С	R	-	-	-	-	N	N	-	-	-	R	-	-
Butyl Phthalate	N	-	-	N	-	-	-	-	-	-	-	-	-	-	-	-
Butylamine, Sal'd	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butylene, liquid	С	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Butyric Acid	R	-	-	-	-	-	-	-	R	R	С	-	-	-	-	-
Butyric Acid, pure	R	-	-	-	-	-	-	-	R	R	С	-	-	-	-	-
С																
Calcium Bisulfide	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Calcium Bisulfite	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-

In the table the figure stands for the below mentioned:



Chemical	PVC					CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Calcium Carbonate	R	R	R	R	R	R	-	-	R	R	R	-	-	-	-	-
Calcium Chlorate	R	R	R	R	-	-	-	-	R	-	-	-	-	-	-	-
Calcium Chloride, Sat'd	R	-	С	R	-	-	-	-	R	R	R	-	С	-	-	-
Calcium Hydroxide,30%	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Calcium Hydroxide, Sat'd	R	R	R	-	-	-	-	-	R	R	R	R	-	-	-	-
Calcium Hypochlorite	-	С	-	-	-	-	-	-	R	R	-	-	-	-	-	-
Calcium Nitrate, Sat'd	R	R	R	R	R	R	-	-	R	-	-	-	-	-	-	-
Calcium Sulfate	R	R	R	R	-	-	-	-	R	-	-	-	-	-	-	-
Calcium Sulfide, Sal'd	R	R	R	R	-	-	-	-	R	-	-	-	-	-	-	-
Camphor Oil	R	-	-	-	-	-	-	-	N	N	N	-	-	-	-	-
Carbon Dioxide, Pure Anhydrous	R	R	R	R	R	R	R	-	R	R	R	R	-	R	R	R
Carbon Dioxide, Pure Moist	R	R	R	R	R	R	R	-	R	R	R	R	-	R	R	R
Carbon Disulfide	С	-	N	N	-	N	-	N	R	-	N	-	N	-	-	-
Carbon Monoxide, Gas	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Carbon Tetrachloride	С	_	N	R	-	-	-	-	N	N	N	-	-	-	-	-
Carbonic Acid, Sat'd	R	R	R	R	-	-	-	-	-	-	-	-	-	-	-	-
Caustic Potash, 50%	R	R	С	-	-	-	-	-	R	R	R	R	R	-	-	-
Caustic Soda, 10%	R	R	С	-	-	-	-	-	R	R	R	R	R	-	-	-
Caustic Soda, 50%	R	R	R	-	-	-	-	-	R	R	R	R	R	-	-	-
Caustic Soda, up to 40%	R	R	С	-	-	-	-	-	R	R	R	R	R	-	-	-
Chloral Hydrate, All	-	-	-	-	-	-	-	-	С	-	-	-	-	-	-	-
Chloramine (Diluted)	R	-	-	R	-	-	-	-	R	-	-	-	-	-	-	-
ChloricAcid, 10%	R	R	С	-	-	-	-	-	-	-	-	-	-	-	-	-
Chloric Acid, 20%	R	R	С	R	-	-	-	-	R	-	N	N	N	-	-	-
Chlorinated Water, 0.3%(Sal'd 1	-	R	R	R	R	R	R	-	С	-	-	-	-	R	R	R
Chlorine, Liquid	N	-	-	-	-	-	-	-	N	N	N	-	-	-	-	-
Chloroacetic Acid, 50%	R	R	С	-	-	-	-	-	R	R	R	-	-	-	-	-
Chlorobenzene, Dry	N	N	N	N	N	-	-	-	N	N	N	-	-	-	-	-
Chloroform, Dry	N	N	-	N	N	N	N	N	С	-	N	-	N	-	-	-
Chlorosulfonic Acid	С	-	N	-	-	-	-	-	N	N	N	N	N	-	-	-
Chrome Alum	R	R	С	R	R	R	R	R	R	R	R	-	С	-	-	-
Chromic Acid, 10%	R	-	С	R	R	R	R	R	R	-	С	-	N	-	-	-
Chromic Acid, 30%	R	-	С	R	R	R	R	R	С	-	N	-	N	-	-	-
Chromic Acid, 50%	R	R	С	R	-	-	-	С	С	-	N	N	N	-	-	-
Cider	R	-	-	R	-	-	-	-	R	-	-	-	-	R	-	-
Coconut Oil	R	R	С	-	-	-	-	-	R	R	R	-	-	-	-	-
Compressed Air	С	-	-	-	-	-	-	-	С	-	-	-	-	R	R	-
Copper Chloride, Sat'd	R	-	R	R	R	R	R	R	R	R	R	-	-	-	-	-
Copper Cyanide	N	N	N	R	-	-	-	-	R	R	R	-	-	-	-	-
Copper Fluoborate	R	R	R	R	-	-	-	-	N	N	N	-	-	-	-	-
Copper Nitrate, 30%	R	-	С	R	-	-	-	-	R	R	R	-	-	-	-	-
Copper Salts	R	R	С	-	-	-	-	-	R	R	С	-	-	R	R	R

 $<sup>\</sup>boldsymbol{R}$  - Stands for recommended |  $\boldsymbol{C}$  - Stands for use with caution |  $\boldsymbol{N}$  - Stands for not recommended

Chemical	PVC					CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Copper Sulfate, Sat'd	R	R	R	R	R	R	-	-	R	R	R	-	-	-	-	-
Cottonseed Oil	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Creosols	С	-	N	С	-	N	-	-	R	-	-	-	-	-	-	-
Creosylic Acid	С	-	N	R	-	-	-	-	-	-	-	-	-	-	-	-
Cresol, 50%	С	-	N	С	-	N	-	-	R	-	-	-	-	-	-	-
Cresol, 90%	N	N	N	N	N	N	-	-	С	-	-	-	-	-	-	-
Cyclohexane	N	N	N	N	N	N	-	-	R	-	С	-	-	R	R	R
Cyclohexanol	R	R	R	-	-	-	-	-	R	R	С	-	-	R	R	R
Cyclohexanone	N	N	N	N	N	N	N	N	R	С	N	N	N	R	С	С
D																
Decahydronaphthalene	R	R	R	-	-	-	-	-	N	N	N	-	-	-	-	-
Detergent, Water Solution	R	R	С	-	-	-	-	-	R	R	R	R	-	-	R	R
Di (Butoxyethyl) Phthalate	N	N	N	N	N	N	-	-	N	-	-	-	-	-	-	-
Dibutyl Phthalate	-	-	-	-	-	-	-	-	R	С	С	-	-	R	С	С
Dibutyl Sebacate	-	-	-	-	-	-	-	-	R	-	-	-	-	R	-	-
Dichloro Ethane	-	-	-	-	-	-	-	-	С	-	-	-	-	С	-	-
Dichlorobenzene	N	N	-	N	-	-	-	-	R	-	-	-	-	-	-	-
Dichloroethylene	N	N	N	-	-	-	-	-	С	-	-	-	-	-	-	-
Diethyl Ether	N	N	N	N	N	N	-	-	R	R	R	-	-	-	-	-
Diglycolic Acid, Sat'd	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Diisobutyl Ketone	-	-	-	-	-	-	-	-	R	-	-	-	-	R	-	-
Dimethylamine	С	-	R	-	-	-	-	-	R	-	С	-	-	-	-	-
Dimethylformamide	С	-	-	-	-	-	-	-	R	-	-	-	-	R	-	С
Dinonyl Phthalate	-	-	-	-	-	-	-	-	R	-	-	-	-	С	-	-
Dioctyl Phthalate	N	N	N	-	-	-	-	-	R	С	С	-	-	С	-	-
Dioxane	-	-	-	-	-	-	-	-	С	С	С	-	-	R	R	R
E																
Ethers	N	N	N	N	N	N	-	-	N	N	N	-	-	-	-	-
Ethyl Acetate	N	N	N	N	N	N	N	N	R	С	С	N	N	R	С	С
Ethyl Alcohol	R	R	С	R	-	-	-	-	R	R	R	R	R	R	R	R
Ethyl Benzene	-	-	-	-	-	-	-	-	С	-	-	-	-	-	-	-
Ethyl Ether	N	N	N	N	N	N	-	-	N	N	N	-	-	-	-	-
Ethylene Chloride	-	-	-	-	-	-	-	-	С	-	-	-	-	С	-	-
Ethylene Chlorohydrin	N	N	N	N	N	N	N	-	-	-	-	-	-	-	-	-
Ethylene Diamine	С	-	-	-	-	-	-	-	R	-	-	-	-	R	R	R
Ethylene Glycol, 100%	R	R	R	N	-	-	-	-	R	R	R	R	R	R	R	R
Ethylene Glycol, 50%	-	-	-	R	R	R	R	-	-	-	-	-	-	-	-	-
Ethylene Oxide	-	-	-	-	-	-	-	-	С	-	-	-	-	-	-	-
Fatty Acids	R	R	R	R	R	R	-	-	R	R	R	-	-	-	-	-
Fatty Alcohol. Sulfamate	R	R	С	-	-	-	-	-	R	R	С	-	-	R	R	R
Ferric Chloride	R	-	С	R	-	-	-	-	R	R	R	-	-	-	-	-
Ferric Chloride, Sat'd	R	R	R	R	R	R	R	R	R	R	R	R	R	_	-	-

In the table the figure stands for the below mentioned:



Chemical		PVC				CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Ferric Nitrate, Sat'd	R	R	R	R	-	-	-	-	-	-	-	-	-	-	-	-
Ferric Sulfate	R	R	R	R	-	-	-	-	R	-	-	-	-	-	-	-
Ferrous Chloride, Sat'd	R	R	R	R	R	R	-	-	R	-	-	-	-	-	-	-
Ferrous Sulfate	R	R	R	R	-	-	-	-	R	-	-	-	-	-	-	-
Fluorine Gas (Dry),100%	С	-	N	-	-	-	-	-	N	N	N	-	-	-	-	-
Fluosilicic Acid, 30%	R	R	R	R	R	R	R	R	R	R	R	-	-	-	-	-
Formaldehyde	R	-	С	R	-	-	-	С	R	R	R	-	-	-	-	-
Formamide	-	-	-	-	-	-	-	-	R	R	R	-	-	R	R	R
Freon 12, 100%	R	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Fruit Juice, Pure	R	R	R	-	-	-	-	-	R	R	R	R	R	R	R	R
Furfuryl Alcohol	-	-	-	-	-	-	-	-	R	-	С	-	-	R	R	R
G																
Gasoline	R	R	С	N	N	N	N	N	N	N	N	N	N	R	R	R
Gelatin	R	R	R	R	-	N	-	-	R	R	R	-	-	R	R	R
Glucose	R	R	С	R	-	-	-	-	R	R	R	R	R	-	-	-
Glycerine	R	R	R	-	-	-	-	-	R	R	R	R	R	R	R	R
Glycine, Aqueous	R	R	R	R	R	R	R	R	R	R	R	R	R	-	-	_
Glycolic Acid, Sat'd	R	-	-	-	-	-	-	-	R	-	-	-	-	R	R	R
Н																
Heptane	R	-	С	R	-	-	-	-	R	-	С	-	-	R	-	С
n-Hexane	R	-	С	R	-	-	-	-	R	-	С	-	-	R	-	С
Hydrazine Hydrate	R	-	-	-	_	-	-	-	R	R	R	-	-	R	R	R
Hydrobromic Acid, 50%	R	R	R	-	-	-	-	-	R	R	R	-	-	R	R	R
HydrochloricAcid, 10%	R	R	С	-	-	-	-	-	R	R	С	С	-	R	R	R
Hydrochloric Acid, 25%	R	-	С	R	R	R	R	R	R	R	R	R	R	-	-	-
Hydrochloric Acid, 36%	R	R	С	-	-	-	-	-	R	С	-	-	-	R	R	R
Hydrochloric Acid, 37%	R	R	R	С	-	R	-	R	R	R	R	-	С	-	-	-
Hydrocyanic Acid	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
HydrofluoricAcid, 10%	R	-	С	R	-	С	-	-	R	R	R	-	N	-	-	-
Hydrofluoric Acid, 60%	С	-	N	R	-	С	-	-	R	-	N	-	N	-	-	-
Hydrogen Peroxide, 30%	R	R	R	R	R	R	R	R	R	R	R	-	-	R	R	R
Hydrogen Sulfide, Dry	R	-	С	-	-	-	-	-	R	R	R	-	-	-	-	-
Hydroxylamine Sulfate	R	R	R	-	-	-	-	-	R	R	R	-	-	R	R	R
1																
lodine	-	-	-	-	-	-	-	-	R	-	-	-	-	R	-	С
Iso butane	R	-	-	-	-	-	-	-	С	-	N	_	-	-	-	-
Isooctane	R	-	-	-	-	-	-	-	R	-	С	-	-	R	-	С
Isopropyl Acetate	R	-	-	-	-	-	-	-	R	R	R	R	R	R	R	R
Isopropyl Alcohol	-	-	С	-	-	-	-	-	R	R	R	-	-	-	-	-
Isopropyl Ether	С	-	N	-	-	-	-	-	С	-	N	_	-	С	-	-
L																
Lactic Acid, 10%	R	С	-	-	-	-	-	-	R	R	R	R	R	R	R	R

 $<sup>\</sup>boldsymbol{R}$  - Stands for recommended |  $\boldsymbol{C}$  - Stands for use with caution |  $\boldsymbol{N}$  - Stands for not recommended

Chemical		PVC				CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Lanolin	R	С	-	-	-	-	-	-	R	R	R	-	-	R	R	R
Lead Acetate, Sat'd	R	R	R	R	R	R	R	R	R		С	С	С	R	R	R
Linseed Oil	R	R	С	R	-	-	-	-	R	R	R	R	R	R	R	R
Liqueurs	R	R	-	-	-	-	-	-	R	-	-	-	-	R	R	-
М																
Magnesium Carbonate	R	-	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Magnesium Chloride, Sat'd	R	R	R	R	R	R	R	R	R	R	R	-	С	-	-	-
Magnesium Hydroxide	R	R	R	R	R	R	R	-	R	R	R	R	-	R	R	R
Magnesium Nitrate	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Magnesium Salts	R	R	С	-	-	-	-	-	R	R	R	R	R	R	R	R
Malic Acid	R	-	-	R	-	-	-	-	R	-	R	-	-	-	-	-
Mercuric Chloride, Sat'd	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Mercuric Cyanide, Sat'd	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Mercurous Nitrate, Sat'd	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Mercury	R	R	R	R	-	-	-	-	R	R	R	-	-	R	R	R
Mercury Salts	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Methane	R	-	-	-	-	-	-	-	R	-	-	-	-	R	-	-
Methyl Acetate	-	-	-	-	-	-	-	-	R	R	R	-	-	R	-	-
Methyl Alcohol	R	R	R	R	-	-	-	-	R	-	С	-	С	-	-	-
Methyl Amine	С	-	N	-	-	-	-	-	R	-	С	-	-	R	-	-
Methyl Bromide	N	-	-	-	-	-	-	-	N	N	N	-	-	-	-	-
Methylene Chloride	N	-	N	N	-	N	-	N	N	-	N	-	N	С	-	-
Methvlsulfuric Acid	R	-	С	R	-	-	-	-	N	-	N	-	N	С	-	-
Milk	R	R	R	R	R	R	R	R	R	R	R	R	R	-	-	-
Molasses	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Morpholine	-	-	-	-	-	-	-	-	R	R	R	-	-	R	R	-
N																
Naphtha	С	-	N	R	-	-	-	-	R	-	N	-	-	-	-	-
Naphthalene	-	-	-	-	-	-	-	-	-	-	-	-	-	R	-	С
Nickel Chloride, Sat'd	R	R	R	R	R	R	R	R	R	R	R	R	R	-	-	-
Nickel Nitrate	R	R	R	R	-	-	-	-	R	R	R	-	С	-	-	-
Nickel Sulfate, Sat'd	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Nitric Acid, 100%	-	-	-	-	-	-	-	-	-	_	-	-	-	-	-	-
Nitric Acid, 40%	R	R	R	R	R	R	R	R	С	-	N	-	N	-	-	-
Nitric Acid, 60%	R	-	С	R	R	R	R	R	С	-	N	-	N	-	-	-
Nitric Acid, 65%	С	С	-	-	-	-	-	-	-	-	-	-	-	С	-	-
Nitrobenzene	N	N	N	N	N	N	-	-	R	-	С	-	-	-	-	-
0																
OleicAcid	R	R	R	R	-	-	-	-	R	R	С	-	-	R	R	С
Oleum	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Olive Oil	R	R	С	-	-	-	-	-	R	R	R	R	R	R	R	С
Oxygen Gas	R	R	R	R	R	R	-	-	N	N	N	-	-	-	-	-

In the table the figure stands for the below mentioned:



Chemical	PVC				CPVC				PPR					HDPE		
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Ozone	R	R	С	R	-	-	-	-	С	N	N	-	-	С	-	-
Р																
Palmitic Acid	R	-	-	-	-	-	-	-	С	-	-	-	-	С	-	-
Palmitic Acid,10%	R	R	R	R	-	-	-	-	-	-	N	-	-	-	-	-
Palmitic Acid, 70%	R	R	R	R	-	-	-	-	-	-	N	-	-	-	-	-
Paraffin	-	-	-	С	-	-	-	-	-	-	R	-	-	-	-	-
Paraffin Emulsion	R	R	R	R	-	-	-	-	R	R	С	-	-	R	R	С
Perchloric Acid, 10%	R	R	R	R	-	-	-	-	R	R	R	-	-	R	R	R
Perchloric Acid, 70%	R	-	С	-	-	-	-	-	R	-	-	-	-	R	R	R
Perchloroethylene	-	-	-	-	-	-	-	-	С	-	-	-	-	С	-	-
Petroleum	R	-	-	-	-	-	-	-	R	С	С	-	-	R	R	С
Phenol, 90%	R	С	-	-	-	-	-	-	R	R	R	-	-	R	R	С
Phenyl Hydrazine	N	N	N	N	N	N	-	-	С	С	С	-	-	С	-	-
Phosgene Gas	R	С	С	-	-	-	-	-	С	-	-	-	-	С	-	-
Phosgene Liquid	-	-	-	-	-	-	-	-	С	-	-	-	-	-	-	-
Phosphoric Acid, 25%	R	-	С	R	-	-	-	С	R	R	R	R	R	-	-	-
Phosphoric Acid, 30%	R	R	С	-	-	-	-	-	R	R	R	R	-	R	R	R
Phosphoric Acid, 50%	R	R	R	R	-	-	-	С	R	R	R	R	R	R	R	R
Phosphoric Acid, 85%	R	R	R	R	-	-	-	С	R	R	R	R	R	R	R	С
Phosphorous Pentoxide	R	R	-	-	-	-	-	-	R	-	-	-	-	R	R	-
Phosphorous Trichloride	N	N	N	N	N	N	-	-	R	-	С	-	-	-	-	-
Phosphorus Oxychloride	-	-	-	-	-	-	-	-	R	-	С	-	-	R	-	С
Phosphorus	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Pentachloride	-	-	-	-	-	-	-	-	R	-	С	-	-	R	-	С
Potassium Bicarbonate	R	R	С	-	-	-	-	-	R	R	R	R	R	R	R	R
Potassium Borate	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Potassium Bromate	R	R	С	R	-	-	-	-	R	R	R	R	R	R	R	С
Potassium Bromide	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Potassium Carbonate	R	R	R	-	-	-	-	-	R	-	-	-	-	-	-	-
Potassium Chlorate	R	R	R	-	-	-	-	-	R	R	R	-	-	R	R	R
Potassium Chloride	R	R	R	-	-	-	-	-	R	R	R	R	R	R	R	R
Potassium Chromate	R	R	R	-	-	-	-	-	R	R	R	-	-	R	-	-
Potassium Cyanide	R	R	R	-	-	-	-	-	R	R	R	-	-	R	R	R
Potassium Ferricyanide	R	R	R	R	-	-	-	-	R	R	R	-	С	-	-	-
Potassium Fluoride	-	-	-	-	-	-	-	-	R	R	R	-	-	-	-	-
Potassium Iodide	R	R	R	-	-	-	-	-	R	R	R	-	-	R	R	R
Potassium Nitrate	R	R	R	R	R	R	R	R	R	R	R	-	-	R	R	R
Potassium Perborate	R	R	R	R	-	-	-	-	R	-	-	-	-	-	-	-
Potassium Perchlorate	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Potassium	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Permanganate, Sat'd	R	R	С	R	R	R	С	-	R	R	С	-	-	R	R	С
Potassium	-	-	-		-	-	-	-	-	-	-	-	-	-	-	-

 $<sup>\</sup>boldsymbol{R}$  - Stands for recommended |  $\boldsymbol{C}$  - Stands for use with caution |  $\boldsymbol{N}$  - Stands for not recommended

Chemical		PVC				CPVC					PPR			HDPE		
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Permanganate, 10%	R	R	С	R	R	R	R	-	R	R	R	R	-	-	-	-
Potassium Persulfate	R	R	С	R	-	-	-	-	R	R	R	-	-	R	R	R
Potassium Sulfate	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Propane	R	-	-	-	-	-	-	-	R	-	-	-	-	R	-	-
1-Propanol	R	С	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Propargyl Alcohol	R	R	R	-	-	-	-	-	R	R	R	-	-	R	R	R
Propionic Acid, 50%	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Propyl Alcohol	R	-	С	R	-	-	-	-	R	R	R	-	-	-	-	-
Propylene Oxide	С	-	-	-	-	-	-	-	R	-	-	-	-	С	-	-
Pyridine	N	N	N	N	N	N	-	-	С	С	С	-	-	-	-	-
S																
Sea Water	R	R	R	R	R	R	R	R	R	R	R	R	R	-	-	-
Silicic Acid	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Silicone Oil	R	R	N	-	-	-	-	-	R	R	R	-	-	R	R	R
Silver Cyanide	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Silver Nitrate	R	-	С	R	R	R	R	R	R	R	R	-	С	-	-	-
Soaps	R	R	С	R	-	-	-	-	R	R	R	-	-	R	R	R
Sodium Acetate, Sat'd	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R	R
Sodium Benzoate	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Sodium Bicarbonate	R	R	R	R	R	R	R	R	R	R	R	R	-	R	R	R
Sodium Bichromate, Sat'd	R	R	R	R	R	R	R	R	R	R	R	R	R	-	-	-
Sodium Bisulfate	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Sodium Bisulfite	R	R	R	R	R	R	R	R	R	R	R	-	С	R	R	R
Sodium Bromide Sat'd	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Sodium Chlorate, Sat'd	R	-	С	R	-	-	-	-	R	R	R	-	-	-	-	-
Sodium Chloride	R	R	С	R	R	R	-	-	R	R	R	R	-	R	-	-
Sodium Chromate	R	R	С	-	-	-	-	-	R	R	-	-	-	R	-	-
Sodium Ferrocyanide, Sat'd 1	-	R	R	R	-	-	-	-	-	-	-	-	-	-	-	-
Sodium Fluoride	R	R	R	R	-	-	-	-	R	-	-	-	-	R	-	-
Sodium Hypochlorite	R	-	С	R	-	-	-	-	R	-	-	-	-	-	-	-
Sodium Iodide	R	R	С	-	-	-	-	-	R	-	-	-	-	R	-	-
Sodium Nitrate, Sat'd	R	R	R	R	-	-	-	-	R	R	R	-	-	R	R	R
Sodium Nitrite, Sat'd	R	-	-	-	-	-	-	-	R	-	-	-	-	R	-	-
Sodium Oxalate	R	R	С	-	-	-	-	-	R	-	-	-	-	R	-	-
Sodium Perborate	R	R	R	R	R	R	R	R	R	-	-	-	-	-	-	-
Sodium Phosphate	R	R	С	-	-	-	-	-	R	R	R	R	R	R	R	R
Sodium Sulfate, Sat'd	R	R	R	R	-	-	-	-	R	R	R	R	-	R	R	R
Sodium Sulfide	R	R	С	R	-	-	-	-	R	R	R	-	-	R	R	R
Sodium Sulfite	R	R	R	R	-	-	-	-	R	R	R	-	-	R	R	R
Sodium Thiosulfate	R	R	С		-	-	-	-	R	R	R	-	-	R	R	R
Stannous Chloride, 15%	R	С	С	-	-	-	-	-	R	R	R	-	-	R	R	R
StearicAcid, 100%	R	R	R	R	R	R	-	-	R	С	С	-	-	R	-	С

In the table the figure stands for the below mentioned:



Chemical	PVC				CPVC				PPR					HDPE		
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Succinic Acid	R	R	R	-	-	-	-	_	R	R	R	_	-	R	R	R
Sugar SvruD	R	R	С	R	-	-	_	_	R	R	R	R	-	R	R	R
Sulfur Dioxide Gas, Dry	R	R	R	R	_	-	-	-	R	R	R	-	N	-	-	_
Sulfur Dioxide Gas, Wet	С	_	N	_	_	-	-	-	-	_	-	-	-	_	-	_
Sulfur Dioxide Liquified	_	_	-	-	_	-	_	-	_	-	-	-	-	_	-	_
Sulfuric Acid, 51% to 60%	R	R	R	_	-	-	_	-	R	R	R	-	-	R	R	R
Sulfuric Acid, 71% to 80%	R	R	R	-	-	-	-	-	R	R	С	-	-	R	R	С
Sulfuric Acid, 96%	R	R	С	R	-	N	-	N	N	N	N	N	N	-	-	-
Sulfuric Acid, 97%	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Sulfurous Acid	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Т																
Tannic Acid	R	-	-	-	-	-	-	-	R	R	R	-	-	R	R	R
Tartaric Acid	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Tetrachloroethane	N	N	N	-	-	-	-	-	С	-	N	-	-	С	-	-
Tetraethyl Lead	R	-	С	R	-	-	-	-	R	-	-	-	-	-	-	_
T etrahyd rofu ran	N	N	N	N	N	N	N	N	С	-	N	-	N	-	-	-
Thionyl Chloride	N	-	-	N	-	-	-	-	N	-	-	-	-	-	-	-
Toluene	N	N	N	N	N	N	N	N	С	N	N	N	N	С	-	-
Transformer Oil	R	-	С	-	-	-	-	-	R	-	С	_	-	-	-	-
Tributyl Phosphate	-	-	-	-	-	-	-	-	R	R	R	-	-	R	R	R
Trichloroacetic Acid	С	-	-	-	-	-	-	-	R	R	R	-	-	R	R	R
Trichloroacetic Acid,50%	R	С	N	-	-	-	-	-	R	R	R	-	-	R	R	R
Trichloroethylene	N	N	N	N	N	N	-	-	N	N	N	-	-	-	-	-
Tricresyl Phosphate	-	-	-	-	-	-	-	-	R	-	С	-	-	R	R	R
Triethanolam ine	С	-	N	-	-	-	-	-	R	-	-	-	-	R	R	R
Triethylamine	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Trioctyl Phosphate	-	-	-	-	-	-	-	-	R	-	-	-	-	С	-	-
Turpentine	R	С	-	-	-	-	-	-	-	-	-	-	-	С	С	С
U																
Urea	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Urea, 30%	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Uric Acid	R	-	С	R	-	С	-	-	-	-	-	-	-	-	-	-
Urine	R	R	С	R	-	-	-	-	R	R	R	-	-	R	R	R
V																
Vaseline	R	-	N	-	-	-	-	-	R	-	С	-	-	-	-	-
Vegetable Oil	R	С	-	-	-	-	-	-	R	R	С	-	-	R	С	-
Vinegar	R	R	R	-	-	-	-	R	-	R	R	R	R	R	R	R
Vinyl Acetate	N	N	N	N	N	N	-	-	R	-	-	-	-	-	-	-
Vinyl Chloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
W																
Water, Deionized	R	R	R	-	-	-	-	-	R	R	R	R	R	R	R	R
Whiskey	R	R	R	R	-	-	-	-	R	-	-	-	-	-	-	-

 $<sup>\</sup>boldsymbol{R}$  - Stands for recommended |  $\boldsymbol{C}$  - Stands for use with caution |  $\boldsymbol{N}$  - Stands for not recommended

Chemical		PVC				CPVC					PPR				HDPE	
Temp in °C	20	40	60	20	40	60	80	100	20	40	60	80	100	20	40	60
Temp in °F	68	104	140	68	104	140	176	212	68	104	140	176	212	68	104	140
Wines	R	R	R	R	R	R	R	R	R	R	R	-	-	-	-	-
X																
Xylene	-	-	-	-	-	-	-	-	R	R	С	-	-	-	-	-
Υ																
Yeast	R	R	-	-	-	-	-	-	R	R	R	-	-	R	R	R
Z																
Zinc Chloride	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Zinc Nitrate	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-
Zinc Salts	R	R	С	-	-	-	-	-	R	R	R	-	-	R	R	R
Zinc Sulfate	R	R	R	R	-	-	-	-	R	R	R	-	-	-	-	-

In the table the figure stands for the below mentioned:

R - Stands for recommended | C - Stands for use with caution | N - Stands for not recommended



Chemical & Concentration Formula	Concentration	ABS	PP	PVC	PE
	85%	-	100	60	23
H₃PO₄	98%	-	-	-	-
Potassium 1	0%	-	82	23	60
Permanganate (KMnO <sub>4</sub> )	25%	-	23	23	60
Soap	-	23	60	60	R to 60
Sodium Bicarbonate (NaHCO <sub>3</sub> )	23%	23	100	60	60
Sodium Carbonate (NaCl)	23	100	60	60	-
Sodium Hypo Chlorite (NaOCIO 5H <sub>2</sub> O)	-	49	23	23	60
	-	-	100	60	60
	30%	49	82	60	60
Sulfur S	50%	23	82	60	49
	60%	C to 23	23	60	49
	70%	C to 23	23	60	R to 49
	80%	C to 23	82	60	R to 49
	90%	C to 23	66	23	49
Sulfuric Acid (H <sub>2</sub> SO <sub>4</sub> )	93%	N	C to 23	23	C to 23
\ 2 4/	94% - 98%	N	C to 23	N	C to 23
	100%	N	C to 23	N	C to 23
Urea	-	-	82	60	60
Urine	-	71	82	60	60
Water, Acid Mild	-	71	60	60	60
H <sub>2</sub> O	-	71	60	60	60
Water (H <sub>2</sub> O), Deionized	-	71	60	60	60
Water (H <sub>2</sub> O), Distilled	-	71	100	100	60
Water (H <sub>2</sub> O), Salt	-	71	100	60	60
Water (H <sub>2</sub> O), Sea	-	71	100	60	60
Water (H <sub>2</sub> O), Soft	-	71	100	60	60
Zinc Sulfate	-	71	82	60	60

#### **RESISTANCE CODES**

Code	Meaning	Typical Results
60	Plastic type is generally resistant to temperature (°C) indicated by code.	Swelling < 3% or weight loss < 0.5% and elongation at break not significantly changed.
R to 23	Plastic type is generally resistant to temperature (°C) indicated by code and may have limited resistance at higher temperatures.	Swelling < 3% or weight loss < 0.5% and elongation at break not significantly have limited resistance at higher temperatures changed.
C to 23	Plastic type is generally resistant to temperature (°C) indicated by code and may be suitable for some conditions	Swelling 3-8% or weight loss < 0.5-5% and / or elongation at break decreased by suitable for some conditions. < 50%.
N	Plastic type is not resistant.	Swelling < 8% or weight loss < 5% and / or elongation at break decreased by > 50%.
-	Data not available	Data not available

- Chemicals that to do not normally affect the properties of an unstressed thermoplastic may cause completely different behavior (such as stress cracking) when under thermal or mechanical stress (such as constant internal pressure or frequent thermal or mechanical stress cycles).
- Unstressed immersion test chemical resistance information is applicable only when the thermoplastic pipe will not be subject to mechanical or thermal stress that is constant or cycles frequently.
- When the pipe will be subject to a continuous applied mechanical or thermal stress or to combinations of chemicals, testing that duplicates the expected field conditions as closely as possible should be performed on representative samples of the pipe product to properly evaluate plastic pipe for use in this application



# **INSTALLATION IMAGES**

### **GREENFIT PP-R INSTALLATION**



### **BLUE GREENFIT PP-R INSTALLATION**





### **AUTHORISED DISTRIBUTOR:**





























Whatsapp No. +91-91670 39334

www.princeenterprise.co.in

### PRINCE ENTERPRISE

Add: Kasturi Complex, Gala No.K-1, Anjur Road Rahnal Village, Bhiwandi, Dist - Thane - 421302,

Office No. +91-7410078051 / 52 / 53.

Email: princeenterprise1@gmail.com